

## Technical Data Sheet

# SustaPPO - ASTM

### Typical industries

- Papírenský průmysl
- Stavební průmysl
- Dopravní technika a automatizace
- Stavba strojů a zařízení
- Elektronika

	Test method	Unit	Guideline value
<b>General properties</b>			
Density	ASTM D792	g / cm <sup>3</sup>	1.08
Water Absorption	ASTM D570	%	0.2
Water Absorption 24 hours	ASTM D570	%	0.07
Dissipation Factor	ASTM D150	1MHz	0.001
<b>Mechanical properties</b>			
Tensile Strength at Yield	ASTM D638	psi	9400
Tensile Modulus	ASTM D638	psi	350000
Tensile Elongation	ASTM D638	%	30
Flexural Strength	ASTM D790	psi	13400
Flexural Modulus	ASTM D790	psi	360000
Rockwell Hardness	ASTM D785	R	119
Izod Impact, Notched	ASTM D256	ft-lb/in	3.5
Coefficient of Friction, Dynamic			0.39
<b>Thermal properties</b>			
Thermal Conductivity		in/hr/ft <sup>2</sup> /°F	1.6
Coefficient of Linear Thermal Expansion	ASTM D696	in/in/°F x10 <sup>-5</sup>	3.3
Continuous Service Temperature, Air		°F	220
Deflection Temperature at 1.8Mpa (264psi)	ASTM D648	°F	260
Deflection Temperature at 1.8Mpa (66psi)	ASTM D648	°F	289
Flammability, UL94		1/8 inch	V-1

### Roehling Industrial Gastonia, LP

903 Gastonia Technology Parkway • 28034 Dallas/United States (US) • Tel. +1 704 922-7814  
[info.gastonia@roehling.com](mailto:info.gastonia@roehling.com) • [www.roehling.com/industrial/rep-us](http://www.roehling.com/industrial/rep-us)

Print: 27/07/2024 • Draft: 21/09/2023

PIM-Version: 22 • PIM-ID: 717971 • PIM-Code: 22-19-8.8.11.5.8



	Test method	Unit	Guideline value
<b>Electrical properties</b>			
Dielectric constant	ASTM D150	1MHz	2.7
Dielectric strength	ASTM D149	V/mil	500
Surface resistivity	ASTM D257	$\Omega/cm$	$10^{17}$
<b>Compliance properties</b>			
FDA			No
NSF			No

