

Technical Data Sheet

SustaPPO MG - ASTM

Typical characteristics

- Biocompatible

Typical industries

- 제지 산업
- 건설업
- 컨베이어 기술 및 자동화
- 기계 공학 산업
- 전자 제품

	Test method	Unit	Guideline value
General properties			
Density	ASTM D792	g / cm ³	1.08
Water Absorption	ASTM D570	%	0.2
Water Absorption 24 hours	ASTM D570	%	0.07
Mechanical properties			
Tensile Strength at Yield	ASTM D638	psi	9400
Tensile Modulus	ASTM D638	psi	350000
Tensile Elongation	ASTM D638	%	30
Flexural Strength	ASTM D790	psi	13400
Flexural Modulus	ASTM D790	psi	360000
Rockwell Hardness	ASTM D785	R	119
Izod Impact, Notched	ASTM D256	ft-lb/in	3.5
Thermal properties			
Thermal Conductivity		in/hr/ft ² /°F	1.6
Coefficient of Linear Thermal Expansion	ASTM D696	in/in/°F x10 ⁻⁵	3.3
Continuous Service Temperature, Air		°F	220
Deflection Temperature at 1.8Mpa (264psi)	ASTM D648	°F	260
Deflection Temperature at 1.8Mpa (66psi)	ASTM D648	°F	289
Flammability, UL94		1/8 inch	V-1
Electrical properties			
Surface resistivity	ASTM D257	Ω/cm	>10 ¹⁷

Röchling Industrial Gastonia, LP

903 Gastonia Technology Parkway • 28034 Dallas/United States (US) • Tel. +1 704 922-7814
 info.gastonia@roechling.com • www.roechling.com/industrial/rep-us

Print: 27/07/2024 • Draft: 21/09/2023

PIM-Version: 25 • PIM-ID: 717972 • PIM-Code: 25-19-16-8.8.11.5.8

Page 1 / 2 (Dates in DD/MM/YYYY)



	Test method	Unit	Guideline value
Compliance properties			
FDA			No
NSF			No

