

## Product information

# Robatube EPDM black

### Further properties

Chemical properties	Guideline Value
Sodium hydroxide (NaOH) 5%	resistant
Hydrochloric acid (HCl) 10%	resistant
Sulphuric acid (H <sub>2</sub> SO <sub>4</sub> ) 10 %	resistant
Formic acid (HCOOH) 10 %	resistant
Diesel oil and oil	not resistant
Turpentine	-
Acetone	not resistant
Other properties	
Flammability	flammable

### Stroke characteristics

Stroke characteristics in mm at 20°C	
Pressure [bar]	Tube diameter [mm]
	15,5
0,5	0,26
1	2,17
1,5	4,49
2	6,55
2,5	8,02

Attention! The characteristic has been determined on the holder with the tare mass of sealing strip.



### Delivery programme

Diameter [mm]	s [mm]	Material
15,5	1,5	EPDM

### Products

Robotube EPDM black

The data given are standard values which are based on our experience and previous studies. These values are influenced by the design, processing conditions and environmental influences out of our control. The sustainability of the material for a given application is the responsibility of the user. Typing and printing errors reserved.

#### Röchling Industrial Oepping GmbH & Co. KG

Röchlingstr. 1 • 4151 Oepping/Austria (AT) • Tel. +43 7289 4611-0  
robaproducts@roebling.com • [www.roebling.com/industrial/oepping](http://www.roebling.com/industrial/oepping)

