

Product information

Robatube ES

Further properties

Chemical properties	Guideline Value
Sodium hydroxide (NaOH) 5%	resistant
Hydrochloric acid (HCl) 10%	resistant
Sulphuric acid (H ₂ SO ₄) 10 %	resistant
Formic acid (HCOOH) 10 %	resistant
Diesel oil and oil	resistant
Turpentine	limited resistant
Acetone	limited resistant
Other properties	
Flammability	flammable

Stroke characteristics

Pressure [bar]	Stroke characteristics in mm at 20°C				Stroke characteristics in mm at 50°C			
	Tube diameter [mm]				Tube diameter [mm]			
	19	22	26	29	19	22	26	29
0,5	0,40	1,20	1,40	1,60	1,00	1,40	1,60	1,80
1	0,90	1,80	2,70	2,70	2,30	2,30	3,10	4,90
1,5	1,70	2,80	4,40	5,00	3,40	4,30	6,00	8,00

Attention! The characteristic has been determined on the holder with the tare mass of sealing strip.



Delivery programme

Diameter [mm]	s [mm]	Material
19	2,7	TPEV
22	2,7	TPEV
26	2,7	TPEV
29	2,9	TPEV

Products

Robatube ES

The data given are standard values which are based on our experience and previous studies. These values are influenced by the design, processing conditions and environmental influences out of our control. The sustainability of the material for a given application is the responsibility of the user. Typing and printing errors reserved.

Röchling Industrial Oepping GmbH & Co. KG

Röchlingstr. 1 • 4151 Oepping/Austria (AT) • Tel. +43 7289 4611-0
 robaproducts@roechling.com • www.roechling.com/industrial/oepping

