

## Technical Data Sheet

# SustaPEEK CM ESD 90 black

### Typical characteristics

- Autoextinguible
- Densidad de humo muy baja
- alta estabilidad dimensional bajo calor

### Typical industries

- Electrónica
- Semiconductor Industry
- Construcción de máquinas e instalaciones
- Healthcare
- Industria aeronáutica y espacial

	Test method	Unit	Guideline value
<b>General properties</b>			
Density	DIN EN ISO 1183-1	g / cm <sup>3</sup>	1,39
<b>Mechanical properties</b>			
Elongation at break	DIN EN ISO 527	%	2,3
Tensile modulus of elasticity	DIN EN ISO 527	MPa	5500
Tensile strength	DIN EN ISO 527	MPa	85
Impact strength	DIN EN ISO 179	kJ / m <sup>2</sup>	15
Notched impact strength	ISO 179-1/1eA	kJ / m <sup>2</sup>	2,6
Shore hardness	DIN EN ISO 868	scale D	85
Elastic modulus of compression	DIN EN ISO 604	MPa	3800
<b>Thermal properties</b>			
Melting temperature	ISO 11357-3	°C	342
<b>Electrical properties</b>			
Volume resistivity	DIN EN 62631-3-1	Ω * cm	10 <sup>6</sup> - 10 <sup>9</sup>
Surface resistivity	DIN EN 62631-3-2	Ω	10 <sup>6</sup> - 10 <sup>9</sup>

The short-term maximum application temperature only applies to very low mechanical stress for a few hours. The long-term maximum application temperature is based on the thermal ageing of plastics by oxidation, resulting in a decrease of the mechanical properties. This applies to an exposure to temperatures for at least 5.000 hours causing a 50% loss of the tensile strength from the original value (measured at room temperature). This value says nothing about the mechanical strength of the material at high application temperatures. In case of thick-walled parts, only the surface layer is affected by oxidation from high temperatures. With the addition of antioxidants, a better protection of the surface layer is achieved. In any case, the center area of the material remains unaffected. The minimum application temperature is basically influenced by possible stress factors like impact and/or shock under application. The values stated refer to a minimum degree of impact stress. The electrical properties as stated result from measurements on natural, dry material. With other colours (in particular black) or saturated material, there may be clear differences in the electrical properties. The data stated above are average values ascertained by statistical tests on a regular basis. They are in accordance with DIN EN 15860. They serve as information about our products and are presented as

### Röchling Industrial Lahnstein SE & Co. KG

Sustaplast-Str. 1 • 56112 Lahnstein/Germany (DE) • Tel. +49 2621 693-0  
[info.lahnstein@roechling.com](mailto:info.lahnstein@roechling.com) • [www.roechling.com/industrial/lahnstein](http://www.roechling.com/industrial/lahnstein)

Print: 22/12/2024 • Release: 18/03/2024 • Version: 2.0  
 PIM-Version: 500 • PIM-ID: 751709 • PIM-Code: 500-45-12.15.11-8.9.5.9.8-6



a guide to choose from our range of materials. This, however, does not include an assurance of specific properties or the suitability for particular application purposes that are legally binding. Since the properties also depend on the dimension of the semi-finished products and the degree of crystallization (e.g. nucleating by pigments), the actual values of the properties of a particular product may differ from the indicated values.



**Röchling Industrial Lahnstein SE & Co. KG**

Sustaplast-Str. 1 • 56112 Lahnstein/Germany (DE) • Tel. +49 2621 693-0  
info.lahnstein@roechling.com • www.roechling.com/industrial/lahnstein

Print: 22/12/2024 • Release: 18/03/2024 • Version: 2.0  
PIM-Version: 500 • PIM-ID: 751709 • PIM-Code: 500-45-12.15.11-8.9.5.9.8-6

Page 2 / 2 (Dates in DD/MM/YYYY)

