

## Produktinformation

# Robaflow<sup>®</sup> C

### Description

Robaflow C is a special material composition used for headbox sheets in paper industry. It consists of Carbon Fiber & Epoxy Resin

Operation Environment	Temperature	Interval	pH value
Continuous Exposure	up to 80°C	24 h/day - 7 days/week	5-10
Cleaning Exposure	up to 90°C	2-4h every 4-6 weeks	either 3-5 or 11-13

### Cleaning information

The material is chemically resistant allowing chemical cleaning (boil-out) without removing. Under condition that above defined parameters for cleaning exposure are not exceeded.

### Produkte

Robaflow<sup>®</sup> C

The data given are standard values which are based on our experience and previous studies. These values are influenced by the design, processing conditions and environmental influences out of our control. The sustainability of the material for a given application is the responsibility of the user. Typing and printing errors reserved.

### Röchling Industrial Oepping GmbH & Co. KG

Röchlingstr. 1 • 4151 Oepping/Austria (AT) • Tel. +43 7289 4611-0  
robaproducts@roechling.com • www.roechling.com/industrial/oepping

