

Technical Data Sheet

EtroX[®] V - ASTM

Typical industries

- Elektronika
- Semiconductor Industry
- Technika [istých prostor]
- Stavba stroj[a za[ízení
- Semiconductor CMP
- Semiconductor High and low temperature
- Semiconductor Back-End applications

	Test method	Unit	Guideline value
General properties			
Moisture	ASTM D6980	%	0.11
Mechanical properties			
Tensile Strength	ASTM D638	psi	14320
Tensile Modulus	ASTM D638	ksi	765
Elongation at Break	ASTM D638	%	3.5
Flexural Strength	ASTM D790	psi	23214
Flexural Modulus	ASTM D790	ksi	791
Thermal properties			
Heat Deflection Temperature	ASTM D648 @ 264psi and 2C/min	°C	>205

