

### Technical Data Sheet

## Fibracon<sup>®</sup> PTFE + 15% Carbon Fibre

#### Typical characteristics

- Low wear when lubricated with water
- Reduced deformation under load compared to virgin PTFE
- Good thermal conductivity
- Electrically conductive

	Test method	Unit	Guideline value
<b>General properties</b>			
Density	ASTM D1457	g / cm <sup>3</sup>	2.0 - 2.2
<b>Mechanical properties</b>			
Hardness	ASTM D1706	Shore D	57 - 63
Tensile Strength (23°C)	ASTM D1457	N/mm <sup>2</sup>	Minimal 14
Elongation CD	ASTM D-1457	%	Minimal 200
<b>Thermal properties</b>			
Service Temperature		°C	-200 to + 260

\*12mm initial gauge used. This data provides typical values on a small selection of properties of the material and should only be used as a guide to the generic material performance.

#### Röchling Industrial (UK) Ltd. – High Peak

Bowden Hey Road - Chapel-en-le-Frith • SK23 0QZ High Peak, Derbyshire/United Kingdom (GB) • Tel. +44 1298 811 800  
[info@roechling-fibracon.co.uk](mailto:info@roechling-fibracon.co.uk) • [www.roechling.com/industrial/high-peak](http://www.roechling.com/industrial/high-peak)

Print: 21/12/2024 • Release: 20/09/2023

PIM-Version: 24 • PIM-ID: 709606 • PIM-Code: 24-40-16.14.3.13-2

Page 1 / 1 (Dates in DD/MM/YYYY)

