

### Technical Data Sheet

## Fibracon<sup>®</sup> PTFE + 40% Bronze green

#### Typical characteristics

- Improved thermal and electrical conductivity
- Reduced chemical resistance
- Reduced deformation under load

	Test method	Unit	Guideline value
<b>Mechanical properties</b>			
Hardness	Needle	Shore D	60-64
Tensile Strength	ASTM D4894	MPa	26
Elongation	ASTM D4894	%	250
<b>Thermal properties</b>			
Service Temperature		°C	-200 to +260

#### Röchling Industrial (UK) Ltd. – High Peak

Bowden Hey Road - Chapel-en-le-Frith • SK23 0QZ High Peak, Derbyshire/United Kingdom (GB) • Tel. +44 1298 811 800  
 info@roechling-fibracon.co.uk • www.roechling.com/industrial/high-peak

Print: 21/12/2024 • Release: 20/09/2023

PIM-Version: 24 • PIM-ID: 709621 • PIM-Code: 24-40-13.13.14

Page 1 / 1 (Dates in DD/MM/YYYY)

