

Technical Data Sheet

Fibracon[®] PTFE + 5% Glass

Typical characteristics

- Reduced deformation under load
- High hardness
- Good wear resistance

	Test method	Unit	Guideline value
General properties			
Specific Gravity	ASTM D4894	-	2.19
Mechanical properties			
Hardness	Needle	Shore D	59
Tensile Strength (Cross Direction)	ASTM D4894	MPa	28
Elongation (Cross Direction)	ASTM D4894	%	320

Typical values - not suitable for specification purposes.

Röchling Industrial (UK) Ltd. – High Peak

Bowden Hey Road - Chapel-en-le-Frith • SK23 0QZ High Peak, Derbyshire/United Kingdom (GB) • Tel. +44 1298 811 800
info@roechling-fibracon.co.uk • www.roechling.com/industrial/high-peak

Print: 21/12/2024 • Release: 20/09/2023

PIM-Version: 27 • PIM-ID: 709622 • PIM-Code: 27-40-14.11.143-2

Page 1 / 1 (Dates in DD/MM/YYYY)

