

Technical Data Sheet

Fibracon[®] PTFE CLF

Typical characteristics

- Bajo desgaste
- No abrasivo
- Bajo coeficiente de fricción

Typical industries

- Construcción de contenedores químico
- Construcción de vehículos
- Electrónica
- Petróleo y gas
- Construcción de máquinas e instalaciones
- Healthcare
- Industria alimentaria
- Energía eólica

	Test method	Unit	Guideline value
General properties			
Specific Gravity	ASTM D4894	-	2.09
Mechanical properties			
Hardness	Needle	Shore D	62
Tensile Strength (Cross Direction)	ASTM D4894	MPa	28
Elongation	ASTM D4894	%	320
Deformation under load	13.7MPa, 23°C 24h	%	8.2
Wear factor	Thrust type / ring on ring P=0.45 MPa, V=1.0 m/s Counter material: Al	10 ⁻⁷ mm ³ / (Nm)	18
Coefficient of friction	Thrust type / ring on ring P=0.45 MPa, V=1.0 m/s Counter material: Al	-	0.15
Thermal properties			
Service Temperature		°C	-200 to +260

Typical values - not suitable for specification purposes.

Röchling Industrial (UK) Ltd. – High Peak

Bowden Hey Road - Chapel-en-le-Frith • SK23 0QZ High Peak, Derbyshire/United Kingdom (GB) • Tel. +44 1298 811 800
 info@roechling-fibracon.co.uk • www.roechling.com/industrial/high-peak

Print: 23/11/2024 • Release: 20/09/2023

PIM-Version: 36 • PIM-ID: 709629 • PIM-Code: 36-40-19.10.12-7.7.8.5.5.9.5.10-2

Page 1 / 1 (Dates in DD/MM/YYYY)

