

### Technical Data Sheet

## Foamlite<sup>®</sup> G 752 + UV-stabilized grey

#### Typical characteristics

- UV-resistant
- Low density
- Nearly no moisture absorption
- Good price-performance ratio

#### Typical industries

- Výroba vozidel
- Stavební průmysl
- Pracovní a rekreační lůžky

	Test method	Unit	Guideline value
<b>General properties</b>			
Density	DIN EN ISO 1183-1	g / cm <sup>3</sup>	0,75
Water absorption	DIN EN ISO 62	%	<0,1
Flammability (Thickness 3 mm / 6 mm)	UL 94		HB
<b>Mechanical properties</b>			
Yield stress	DIN EN ISO 527	MPa	>15
Tensile modulus of elasticity	DIN EN ISO 527	MPa	>600
Notched impact strength	DIN EN ISO 179	kJ / m <sup>2</sup>	>6
Shore hardness	DIN EN ISO 868	scale D	>62
<b>Thermal properties</b>			
Melting temperature	ISO 11357-3	°C	133 ... 135
Thermal conductivity	DIN 52612-1	W / (m * K)	0,30 - 0,40
Thermal capacity	DIN 52612	kJ / (kg * K)	1,90
Coefficient of linear thermal expansion	DIN 53752	10 <sup>-6</sup> / K	150 ... 230
Service temperature, long term	Average	°C	-30 ... 80
Service temperature, short term (max.)	Average	°C	100
Vicat softening temperature	DIN EN ISO 306, Vicat B	°C	67
<b>Electrical properties</b>			
Dielectric constant	IEC 60250		2,5
Dielectric dissipation factor (10 <sup>6</sup> Hz)	IEC 60250		0,0004
Volume resistivity	DIN EN 62631-3-1	Ω * cm	>10 <sup>14</sup>
Surface resistivity	DIN EN 62631-3-2		>10 <sup>14</sup>

#### Röchling Industrial SE & Co. KG

Röchlingstr. 1 • 49733 Haren (Ems)/Germany (DE) • Tel. +49 5934 701-0  
[info@roechling-plastics.com](mailto:info@roechling-plastics.com) • [www.roechling.com/industrial/haren](http://www.roechling.com/industrial/haren)

Print: 05/07/2024 • Draft: 05/07/2024

PIM-Version: 464 • PIM-ID: 718608 • PIM-Code: 464-8-14.12.9.10-7.8.11-5

Page 1 / 2 (Dates in DD/MM/YYYY)



The data stated above are average values ascertained by statistical tests on a regular basis. They are in accordance with DIN EN 15860. The data above are provided purely for information and shall not be regarded as binding unless expressly agreed in a contract of sale.



**Röchling Industrial SE & Co. KG**

Röchlingstr. 1 • 49733 Haren (Ems)/Germany (DE) • Tel. +49 5934 701-0  
info@roechling-plastics.com • www.roechling.com/industrial/haren

Print: 05/07/2024 • Draft: 05/07/2024

PIM-Version: 464 • PIM-ID: 718608 • PIM-Code: 464-8-14.12.9.10-7.8.11-5

Page 2 / 2 (Dates in DD/MM/YYYY)

