

Technical Data Sheet

Glastherm[®] HT 200 - ASTM

Typical characteristics

- Fibre-reinforced composite material developed for applications in field of thermal insulation (max. continuous operating temperature 200°C)
- Reduces Heat Loss
- Low thermal conductivity and extremely high heat resistance

Typical industries

- Химическая промышленность
- Машиностроение
- Нефтепроводы
- Нефтегазовая отрасль

	Test method	Unit	Guideline value
General properties			
Part Number			3913 / 3915
Standard Color			White or Green
Maximum Service Temp.		°C	288
Continuous Use Temp.		°C	200
Mechanical properties			
Flexural Strength	ASTM D 790	psi	31,000
Compressive Strength @75°F / 24°C	ASTM D 695	psi	49,000
Compressive Strength @302°F / 150°C	ASTM D 695	psi	27,000
Compressive Strength @392°F / 200°C	ASTM D 695	psi	18,000
Compressive Strength @550°F / 288°C	ASTM D 695	psi	17,000
IZOD Impact Strength (notched)	ASTM D 256	ft. lb./in.	8
Thermal properties			
Coefficient of Thermal Expansion Across Thickness	ASTM D 696	(in./in.°C) x 10-5	11.62
Coefficient of Thermal Expansion Across Surface	ASTM D 696	(in./in.°C) x 10-5	2.21
Thermal Conductivity	ASTM C 177		1.9
Flame resistance properties			
UL Subject 94	UL 94		HB



	Test method	Unit	Guideline value
Physical properties			
Density	ASTM D 792	lbs/ft ³	123
Water Absorption	ASTM D 570	% by wt.	0.2
Thickness Tolerance		inches	+/-0.002
Dielectrical properties			
Electrical Strength - Perpendicular S/T in Air	ASTM D 149	Vpm	50

All of the information, suggestions, and recommendations pertaining to the properties and uses of the Röchling Glastic Composites products described herein are based upon tests and data believed to be accurate; however, the final determination regarding the suitability of any material described herein for the use contemplated, the manner of such use, and whether the use infringes any patents is the sole responsibility of the user. THERE IS NO WARRANTY, EXPRESS OR IMPLIED, INCLUDING, WITHOUT LIMITATION WARRANTY OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE. Under no circumstances shall we be liable for incidental or consequential loss or damage. Glastic® is a registered trademark of Röchling Glastic Composites. UL® is a registered trademark of Underwriters Laboratories, Inc.



Röchling Industrial Cleveland, LP

4321 Glenridge Road • 44121 Cleveland/United States (US) • Tel. +1 216 486-0100
 info@glastic.com • www.roechling.com/cleveland

Print: 27/07/2024 • Release: 11/10/2023 • Version: 1.0
 PIM-Version: 59 • PIM-ID: 715299 • PIM-Code: 59-25-8.6.6-7.5.5.5-6

