

Technical Data Sheet

Glastic® 1120

Typical characteristics

- UL® Recognized
- High Strength
- Corrosion resistant

Typical industries

- Industrie du bâtiment et des travaux publics
- Fume Hood Liners
- Chemical Storage Cabinets

	Test method	Unit	Guideline value
General properties			
Standard Color			White
UL Recognition File Number			R9599
Mechanical properties			
Flexural Strength	ASTM D 790	psi	22,100
Flexural Strength @130°C	ASTM D 790	psi	13,100
Compressive Strength	ASTM D 695	psi	33,100
Tensile Strength	ASTM D 638	psi	7,800
IZOD Impact Strength (notched)	ASTM D 256	ft. lb./in.	8.9
Thermal properties			
Coefficient of Thermal Expansion	ASTM D 696	(in./in.°C) x 10-5	2
Thermal Conductivity	ASTM C 177		1.9
Flame resistance properties			
Tunnel Test - Flame Spread - U.S. Calculation	ASTM E 84		15
Tunnel Test - Flame Spread - Canadian Calculation	ASTM E 84		20
Smoke Developed	ASTM E 84		500+
Physical properties			
Water Absorption	ASTM D 570	% by wt.	0.4
Specific Gravity	ASTM D 792		1.81

All of the information, suggestions, and recommendations pertaining to the properties and uses of the Röchling Glastic Composites products described herein are based upon tests and data believed to be accurate; however, the final determination regarding the suitability of any material described herein for the use contemplated, the manner of such use, and whether the use infringes any patents is the sole responsibility of the user. THERE IS NO WARRANTY, EXPRESS OR IMPLIED, INCLUDING, WITHOUT LIMITATION WARRANTY OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE. Under no circumstances shall we be liable for incidental or consequential loss or damage. Glastic® is a registered trademark of Röchling Glastic Composites. UL® is a registered trademark of Underwriters Laboratories, Inc.

