

## Technical Data Sheet

# Glastic® SG-200 Corner Angles

### Typical characteristics

- Extremely strong, excellent retention of properties at elevated temperature, easily fabricated
- Dimensionally Stable

### Typical industries

- Generator and Motor
- Dry transformers
- 전기 산업
- Electrical Insulating Components
- Switchgear
- Transformer

	Test method	Unit	Guideline value
<b>General properties</b>			
Standard Color			Tan
UL Temperature Index - Electrical	UL 746B	°C	210
UL Temperature Index - Mechanical	UL 746B	°C	210
<b>Mechanical properties</b>			
Flexural Strength	ASTM D 790	psi	80,000
Tensile Strength	ASTM D 638	psi	70,000
Tensile Modulus	ASTM D 638	psi X 10 <sup>6</sup>	3
IZOD Impact Strength (notched)	ASTM D 256	ft. lb./in.	40
In-Plane Shear Strength	ASTM D 3914	psi	3,000
Compressive Strength - Axial	ASTM D 695	psi	50,000
Compressive Strength - Transverse	ASTM D 695	psi	14,000
<b>Thermal properties</b>			
Coefficient of Thermal Expansion	ASTM D 696	(in./in.°C) x 10 <sup>-5</sup>	0.7
Thermal Conductivity	ASTM C 177		2
<b>Flame resistance properties</b>			
UL Subject 94	UL 94		HB
<b>Physical properties</b>			
Specific Gravity	ASTM D 792		1.85
Water Absorption	ASTM D 570	%	0.15



	Test method	Unit	Guideline value
<b>Dielectrical properties</b>			
Arc Resistance	ASTM D 495	sec.	150
Permittivity, 60 Hz	ASTM D 150		5
Insulation Resistance	ASTM D 257	$\Omega \times 10^{12}$	64
Electrical Strength - Axial in Oil		kV	70

All of the information, suggestions, and recommendations pertaining to the properties and uses of the Röchling Glastic Composites products described herein are based upon tests and data believed to be accurate; however, the final determination regarding the suitability of any material described herein for the use contemplated, the manner of such use, and whether the use infringes any patents is the sole responsibility of the user. THERE IS NO WARRANTY, EXPRESS OR IMPLIED, INCLUDING, WITHOUT LIMITATION WARRANTY OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE. Under no circumstances shall we be liable for incidental or consequential loss or damage. Glastic® is a registered trademark of Röchling Glastic Composites. UL® is a registered trademark of Underwriters Laboratories, Inc. See correlating profile page for sizing and related information.

