

Technical Data Sheet

Glastic® T-160

Typical characteristics

- Alta resistencia
- NEMA GPO-1
- Resistente al calor

Typical industries

- Sector eléctrico
- Componentes de aislamiento eléctrico
- Electrónica

	Test method	Unit	Guideline value
General properties			
Part Number			1360
NEMA Grade LI 1-1989	NEMA LI-1		GPO-1
Standard Color			Natural
Mechanical properties			
Flexural Strength	ASTM D 790	psi	29,000
Flexural Strength @130°C	ASTM D 790	psi	25,000
Compressive Strength	ASTM D 695	psi	56,000
Tensile Strength	ASTM D 638	psi	14,000
IZOD Impact Strength (notched)	ASTM D 256	ft. lb./in.	12
Bond Strength	ASTM D 229	lbs.	1,790
Flame resistance properties			
UL Subject 94	UL 94		HB
Physical properties			
Water Absorption	ASTM D 570	% by wt.	0.3
Specific Gravity	ASTM D 792		1.9
Dielectrical properties			
Electrical Strength - Perpendicular S/T in Air	ASTM D 149	Vpm	270
Electrical Strength - Perpendicular S/T in Oil	ASTM D 149	Vpm	412
Electrical Strength - Parallel S/S in Oil	ASTM D 149	kV	40
Arc Resistance	ASTM D 495	sec.	140

All of the information, suggestions, and recommendations pertaining to the properties and uses of the Röchling Glastic Composites products described herein are based upon tests and data believed to be accurate; however, the final determination regarding the suitability of any material described herein for the use contemplated, the manner of



such use, and whether the use infringes any patents is the sole responsibility of the user. THERE IS NO WARRANTY, EXPRESS OR IMPLIED, INCLUDING, WITHOUT LIMITATION WARRANTY OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE. Under no circumstances shall we be liable for incidental or consequential loss or damage. Glastic® is a registered trademark of Röchling Glastic Composites. UL® is a registered trademark of Underwriters Laboratories, Inc.



Röchling Industrial Cleveland, LP

4321 Glenridge Road • 44121 Cleveland/United States (US) • Tel. +1 216 486-0100
info@glastic.com • www.roechling.com/cleveland

Print: 27/07/2024 • Release: 20/09/2023 • Version: 1.0
PIM-Version: 42 • PIM-ID: 715320 • PIM-Code: 42-23-6.9.6-11.7.8-6

Page 2 / 2 (Dates in DD/MM/YYYY)

