

Technical Data Sheet

Laminex[®] 2010

Typical characteristics

- High rigidity
- Good electrical properties
- Good resistance to oil and fuel

Typical industries

- Construction de machines et d'installations

| | Test method | Unit | Guideline value |
|-------------------------------|-------------------|---------------------|-----------------|
| General properties | | | |
| Densité | DIN EN ISO 1183-1 | g / cm ³ | 1,35-1,40 |
| Mechanical properties | | | |
| Bending strength | DIN EN ISO 178 | MPa | 100-140 |
| Tensile modulus of elasticity | DIN EN ISO 527 | MPa | 5000-7100 |
| Tensile modulus of bending | DIN EN ISO 178 | MPa | 6500-8200 |
| Notched impact strength | DIN EN ISO 179 | kJ / m ² | 6,5-16 |
| Elongation at break | DIN EN ISO 527 | % | 1,3-3,0 |

Röchling Industrial Xanten GmbH

Hagdornstraße 3 • 46509 Xanten/Germany (DE) • Tel. +49 2801 76-0
 info-xan@roechling.com • www.roechling.com/industrial/xanten

Print: 21/12/2024 • Release: 20/09/2023 • Version: 1.0
 PIM-Version: 44 • PIM-ID: 715328 • PIM-Code: 44-24-11.10.14-5

