

Technical Data Sheet

LubX[®] AST white

Typical characteristics

- Anti estático
- Buenas propiedades de deslizamiento
- Excelentes propiedades de funcionamiento en seco
- Buena resistencia al desgaste

Typical industries

- Construcción de máquinas e instalaciones
- Sistemas de transporte y automatización
- Industria alimentaria
- Productos de bollería y dulces
- Industria de bebidas

	Test method	Unit	Guideline value
General properties			
Density	DIN EN ISO 1183-1	g / cm ³	0,95
Water absorption	DIN EN ISO 62	%	<0,01
Flammability (Thickness 3 mm / 6 mm)	UL 94		HB
Non-toxicity			+
Moulding Compound PE	DIN ISO 1872-1		UHMW-PE-QCD 35-3-4
Mechanical properties			
Yield stress	DIN EN ISO 527	MPa	15
Elongation at yield stress	DIN EN ISO 527	%	23
Tensile modulus of elasticity	DIN EN ISO 527	MPa	510
Impact strength	DIN EN ISO 179	kJ / m ²	50
Shore hardness	DIN EN ISO 868	scale D	60
Thermal properties			
Melting temperature	ISO 11357-3	°C	133 - 135
Coefficient of linear thermal expansion	DIN 53752	10 ⁻⁶ / K	150 - 230 (*)
Service temperature, long term	Average	°C	-150 ... 80 (*)
Service temperature, short term (max.)	Average	°C	130 (*)
Electrical properties			
Volume resistivity	DIN EN 62631-3-1	Ω * cm	≤10 ⁹

Röchling Industrial SE & Co. KG

Röchlingstr. 1 • 49733 Haren (Ems)/Germany (DE) • Tel. +49 5934 701-0
 info@roechling-plastics.com • www.roechling.com/industrial/haren

Print: 03/07/2024 • Draft: 03/07/2024

PIM-Version: 438 • PIM-ID: 718574 • PIM-Code: 438-8-15.222.12.142-5.11.5.6-5

Page 1 / 2 (Dates in DD/MM/YYYY)



	Test method	Unit	Guideline value
Surface resistivity	DIN EN 62631-3-2		$\leq 10^9$

The data stated above are average values ascertained by statistical tests on a regular basis. They are in accordance with DIN EN 15860. The data above are provided purely for information and shall not be regarded as binding unless expressly agreed in a contract of sale.



Röchling Industrial SE & Co. KG

Röchlingstr. 1 • 49733 Haren (Ems)/Germany (DE) • Tel. +49 5934 701-0
info@roechling-plastics.com • www.roechling.com/industrial/haren

Print: 03/07/2024 • Draft: 03/07/2024

PIM-Version: 438 • PIM-ID: 718574 • PIM-Code: 438-8-15.222.12.142-5.11.5.5.6-5

Page 2 / 2 (Dates in DD/MM/YYYY)

