

Technical Data Sheet

LubX[®] C C blue pressed

Typical characteristics

- Energy-saving
- Especially aligned to POM and Steel
- FDA/21CFR177.1520 compliant
- Noise-reducing
- Coefficient of friction with POM as sliding partner up to 75% less than of PE-UHMW
- Coefficient of friction with steel as sliding partner up to 60% less than of PE-UHMW
- Food compliant according to 10/2011/EU, 1935/2004/EC, FDA

Typical industries

- Mechanical Engineering Industry
- Building industry
- Conveyor Technology & Automation
- Food Industry
- Bakery and Confectionery
- Beverage Industry

	Test method	Unit	Guideline value
General properties			
Density	DIN EN ISO 1183-1	g / cm ³	0,93
Water absorption	DIN EN ISO 62	%	<0,01
Flammability (Thickness 3 mm / 6 mm)	UL 94		HB
Non-toxicity			+
Moulding Compound PE	DIN ISO 1872-1		UHMW-PE-QCD 35-3-4
Mechanical properties			
Sliding properties: partner POM (0,25 m/s - 0,25 MPa)	REP - Tribology - Test		0,08
Sliding properties: partner POM (0,25 m/s - 0,25MPa)	REP - Tribology - Test		0,11
Yield stress	DIN EN ISO 527	MPa	20
Elongation at break	DIN EN ISO 527	%	>50
Tensile modulus of elasticity	DIN EN ISO 527	MPa	500
Notched impact strength	DIN EN ISO 179	kJ / m ²	no break
Shore hardness	DIN EN ISO 868	scale A	60
Shore hardness	DIN EN ISO 868	scale D	60

Röchling Industrial SE & Co. KG

Röchlingstr. 1 • 49733 Haren (Ems)/Germany (DE) • Tel. +49 5934 701-0
 info@roechling-plastics.com • www.roechling.com/industrial/haren

Print: 23/11/2024 • Release: 20/09/2023 • Version: 3.0
 PIM-Version: 179 • PIM-ID: 710096 • PIM-Code: 179-26-12.10.21.13.13.11.11-5.8.11.5.5.6



	Test method	Unit	Guideline value
Thermal properties			
Melting temperature	ISO 11357-3	°C	133 ... 135
Coefficient of linear thermal expansion	DIN 53752	10 ⁻⁶ / K	150 - 230 (*)
Service temperature, long term	Average	°C	-150 ... 80 (*)
Service temperature, short term (max.)	Average	°C	130 (*)
Electrical properties			
Volume resistivity	DIN EN 62631-3-1	Ω * cm	>10 ¹⁵
Volume resistivity	DIN EN 62631-3-1	Ω * cm	>10 ¹⁵
Surface resistivity	DIN EN 62631-3-2		>10 ¹⁴



Röchling Industrial SE & Co. KG

Röchlingstr. 1 • 49733 Haren (Ems)/Germany (DE) • Tel. +49 5934 701-0
 info@roechling-plastics.com • www.roechling.com/industrial/haren

Print: 23/11/2024 • Release: 20/09/2023 • Version: 3.0
 PIM-Version: 179 • PIM-ID: 710096 • PIM-Code: 179-26-12.10.21.13.13.11.11-5.8.11.5.5.6

