

Technical Data Sheet

LubX[®] CV blue extruded

Typical characteristics

- Good sliding properties even at higher load
- Good dry-running properties
- Food compliant according to 10/2011/EU, 1935/2004/EC, FDA
- Good machinability
- GMP 2023/2006 EC compliant

Typical industries

- Construction de machines et d'installations
- Industrie papetière
- Systèmes de convoyage et automatisation
- Industrie agroalimentaire
- La transformation des viandes, des poissons, des volailles
- Produits de boulangerie et de confiserie
- Industrie des boissons

	Test method	Unit	Guideline value
General properties			
Densité	DIN EN ISO 1183-1	g / cm ³	0,94
Water absorption	DIN EN ISO 62	%	<0,01
Flammability (Thickness 3 mm / 6 mm)	UL 94		HB
Non-toxicity			+
Mechanical properties			
Yield stress	DIN EN ISO 527	MPa	19
Elongation at break	DIN EN ISO 527	%	>250
Tensile modulus of elasticity	DIN EN ISO 527	MPa	500
Notched impact strength	DIN EN ISO 179	kJ / m ²	no break
Shore hardness	DIN EN ISO 868	scale D	60
Sliding properties: partner POM (0,5 m/s - 0,5 MPa)	REP – Tribology – Test		0,13
Thermal properties			
Melting temperature	ISO 11357-3	°C	133 – 135
Coefficient of linear thermal expansion	DIN 53752	10 ⁻⁶ / K	150 - 230 (*)
Service temperature, long term	Average	°C	-150 ... 80 (*)

	Test method	Unit	Guideline value
Service temperature, short term (max.)	Average	°C	130 (*)
Electrical properties			
Volume resistivity	DIN EN 62631-3-1	$\Omega \cdot \text{cm}$	$>10^{15}$
Surface resistivity	DIN EN 62631-3-2	Ω	$>10^{14}$

The data stated above are average values ascertained by statistical tests on a regular basis. They are in accordance with DIN EN 15860. The data above are provided purely for information and shall not be regarded as binding unless expressly agreed in a contract of sale. (*) literature values

