

Technical Data Sheet

Maywotron[®] XT H

Typical characteristics

- Electrically conductive

Typical industries

- Вакуумная формовка
- Электронная промышленность

	Test method	Unit	Guideline value
General properties			
Density	DIN EN ISO 1183-1	g / cm ³	1,04
Water absorption	DIN EN ISO 62	%	<0,1
Mechanical properties			
Yield stress	DIN EN ISO 527	MPa	18
Elongation at yield stress	DIN EN ISO 527	%	1,1
Elongation at break	DIN EN ISO 527	%	47,9
Tensile modulus of elasticity	DIN EN ISO 527	MPa	2021
Notched impact strength	DIN EN ISO 179	kJ / m ²	7,1
Thermal properties			
Melting temperature	ISO 11357-3	°C	>170°C
Thermal conductivity	DIN 52612-1	W / (m * K)	0,17
Coefficient of linear thermal expansion	DIN 53752	10 ⁻⁶ / K	90
Vicat softening temperature	DIN EN ISO 306, Vicat B	°C	98
Electrical properties			
Surface resistivity	DIN EN 61340	Ω	10 ² - 10 ⁴
Volume resistivity	DIN EN 61340	Ω	10 ² - 10 ⁴

Röchling Industrial Allgäu GmbH

Hinter den Gärten 20 • 87730 Bad Grönenbach/Germany (DE) • Tel. +49 8334 9857-0
 info@roechling-maywo.de • www.roechling.com/industrial/groenenbach

Print: 28/10/2024 • Release: 26/09/2024 • Version: 4.0
 PIM-Version: 54 • PIM-ID: 773554 • PIM-Code: 54-15-13-4.8

