

### Technical Data Sheet

## Polystone<sup>®</sup> D Naturel - ASTM

#### Typical characteristics

- Good mechanical properties
- Very wear, cutting and scratch resistant
- Good sliding properties

#### Typical industries

- Construction de machines et d'installations
- Industrie agroalimentaire
- Produits de boulangerie et de confiserie

	Test method	Unit	Guideline value
<b>General properties</b>			
Densité	ASTM D792	g / cm <sup>3</sup>	0.94
Carbon Black Content	ISO6964	%	n/a
<b>Mechanical properties</b>			
Hardness	ASTM D2240	Shore D	63-69
Flexural Modulus	ASTM D790	psi	150000
Izod Impact Strength	D4020		9
<b>Thermal properties</b>			
Melting Point		°F	275-280
Maximum Service Temperature, Air		°F	180
Coefficient of Linear Thermal Expansion	ASTM D696	in/in/°F x10 <sup>-4</sup>	1.9

#### Röchling Industrial Gastonia, LP

903 Gastonia Technology Parkway • 28034 Dallas/United States (US) • Tel. +1 704 922-7814  
 info.gastonia@roechling.com • www.roechling.com/industrial/rep-us

Print: 27/07/2024 • Release: 31/05/2024 • Version: 1.0  
 PIM-Version: 38 • PIM-ID: 717983 • PIM-Code: 38-18-16.40.222-5.5.5

