

### Technical Data Sheet

## Polystone<sup>®</sup> D brown

#### Typical characteristics

- Good mechanical properties
- Good sliding properties
- Good wear resistance
- Good cutting resistance
- High scratch resistance
- Physiologically safe

#### Typical industries

- Construction de machines et d'installations
- Industrie agroalimentaire
- La transformation des viandes, des poissons, des volailles
- Produits de boulangerie et de confiserie

	Test method	Unit	Guideline value
<b>General properties</b>			
Densité	DIN EN ISO 1183-1	g / cm <sup>3</sup>	>0,95
Water absorption	DIN EN ISO 62	%	<0,01
Flammability (Thickness 3 mm / 6 mm)	UL 94		HB
<b>Mechanical properties</b>			
Yield stress	DIN EN ISO 527	MPa	>27
Elongation at break	DIN EN ISO 527	%	>50
Tensile modulus of elasticity	DIN EN ISO 527	MPa	>1200
Shore hardness	DIN EN ISO 868	scale D	65
<b>Thermal properties</b>			
Melting temperature	ISO 11357-3	°C	130 ... 135
Thermal conductivity	DIN 52612-1	W / (m * K)	0,40
Thermal capacity	DIN 52612	kJ / (kg * K)	1,90
Coefficient of linear thermal expansion	DIN 53752	10 <sup>-6</sup> / K	150 ... 230
Service temperature, long term	Average	°C	-100 ... 80
Service temperature, short term (max.)	Average	°C	80
Vicat softening temperature	DIN EN ISO 306, Vicat B	°C	79
<b>Electrical properties</b>			
Dielectric constant	IEC 60250		2,3
Dielectric dissipation factor (10 <sup>6</sup> Hz)	IEC 60250		0,0002

	Test method	Unit	Guideline value
Volume resistivity	DIN EN 62631-3-1	$\Omega \cdot \text{cm}$	$>10^{14}$
Surface resistivity	DIN EN 62631-3-2	$\Omega$	$>10^{14}$
Comparative tracking index	IEC 60112		600
Dielectric strength	IEC 60243	kV / mm	$>40$

The data stated above are average values ascertained by statistical tests on a regular basis. They are in accordance with DIN EN 15860. The data above are provided purely for information and shall not be regarded as binding unless expressly agreed in a contract of sale.



#### Röchling Industrial SE & Co. KG

Röchlingstr. 1 • 49733 Haren (Ems)/Germany (DE) • Tel. +49 5934 701-0  
[info@roechling-plastics.com](mailto:info@roechling-plastics.com) • [www.roechling.com/industrial/haren](http://www.roechling.com/industrial/haren)

Print: 21/11/2024 • Release: 30/04/2024 • Version: 9.0  
 PIM-Version: 728 • PIM-ID: 591112 • PIM-Code: 728-15-17.223.143.9.23.11-5.5.5.5-5

