

### Technical Data Sheet

# Polystone<sup>®</sup> D nuclear black

#### Typical characteristics

- Shielding against neutron radiation
- Good mechanical properties

#### Typical industries

- Jaderný průmysl

	Test method	Unit	Guideline value
<b>General properties</b>			
Density	DIN EN ISO 1183-1	g / cm <sup>3</sup>	>1,05
Flammability (Thickness 3 mm / 6 mm)	UL 94		HB
Boron content	Elemental analysis	% by weight	>5
<b>Mechanical properties</b>			
Yield stress	DIN EN ISO 527	MPa	>20
Tensile modulus of elasticity	DIN EN ISO 527	MPa	>1400
Shore hardness	DIN EN ISO 868	scale D	67
<b>Thermal properties</b>			
Melting temperature	ISO 11357-3	°C	130 ... 135
Thermal conductivity	DIN 52612-1	W / (m * K)	0,40
Thermal capacity	DIN 52612	kJ / (kg * K)	1,90
Coefficient of linear thermal expansion	DIN 53752	10 <sup>-6</sup> / K	150 ... 230
Service temperature, long term	Average	°C	-100 ... 80
Service temperature, short term (max.)	Average	°C	100
Vicat softening temperature	DIN EN ISO 306, Vicat B	°C	79
<b>Electrical properties</b>			
Volume resistivity	DIN EN 62631-3-1	Ω * cm	>10 <sup>14</sup>
Surface resistivity	DIN EN 62631-3-2		>10 <sup>14</sup>
Comparative tracking index	IEC 60112		600

The data stated above are average values ascertained by statistical tests on a regular basis. They are in accordance with DIN EN 15860. The data above are provided purely for information and shall not be regarded as binding unless expressly agreed in a contract of sale.

#### Röchling Industrial SE & Co. KG

Röchlingstr. 1 • 49733 Haren (Ems)/Germany (DE) • Tel. +49 5934 701-0  
[info@roechling-plastics.com](mailto:info@roechling-plastics.com) • [www.roechling.com/industrial/haren](http://www.roechling.com/industrial/haren)

Print: 27/07/2024 • Release: 20/09/2023

PIM-Version: 510 • PIM-ID: 591228 • PIM-Code: 510-18-10.16-6-5

Page 1 / 1 (Dates in DD/MM/YYYY)

