

Technical Data Sheet

Polystone[®] E natural extruded

Typical characteristics

- Easy processing
- High flexibility
- High elongation at break
- Good impact strength

Typical industries

- Ingegneria meccanica e impiantistica
- Healthcare
- Tecnica di imbutitura

| | Test method | Unit | Guideline value |
|--|-------------------|----------------------|-------------------|
| General properties | | | |
| Density | DIN EN ISO 1183-1 | g / cm ³ | 0,92 |
| Water absorption | DIN EN ISO 62 | % | <0,1 |
| Flammability (Thickness 3 mm / 6 mm) | UL 94 | | HB |
| Mechanical properties | | | |
| Elongation at break | DIN EN ISO 527 | % | >50 |
| Tensile modulus of elasticity | DIN EN ISO 527 | MPa | >200 |
| Notched impact strength | DIN EN ISO 179 | kJ / m ² | >60 |
| Shore hardness | DIN EN ISO 868 | scale D | >40 |
| Thermal properties | | | |
| Melting temperature | ISO 11357-3 | °C | 105 ... 115 |
| Thermal conductivity | DIN 52612-1 | W / (m * K) | 0,35 |
| Thermal capacity | DIN 52612 | kJ / (kg * K) | 2,10 |
| Coefficient of linear thermal expansion | DIN 53752 | 10 ⁻⁶ / K | 150 ... 230 |
| Service temperature, long term | Average | °C | -50 ... 60 |
| Service temperature, short term (max.) | Average | °C | 90 |
| Electrical properties | | | |
| Dielectric constant | IEC 60250 | | 2,4 |
| Dielectric dissipation factor (10 ⁶ Hz) | IEC 60250 | | 0,0006 |
| Volume resistivity | DIN EN 62631-3-1 | Ω * cm | >10 ¹⁴ |
| Surface resistivity | DIN EN 62631-3-2 | Ω | >10 ¹⁴ |
| Comparative tracking index | IEC 60112 | | 600 |

| | Test method | Unit | Guideline value |
|---------------------|-------------|---------|-----------------|
| Dielectric strength | IEC 60243 | kV / mm | >40 |

The data stated above are average values ascertained by statistical tests on a regular basis. They are in accordance with DIN EN 15860. The data above are provided purely for information and shall not be regarded as binding unless expressly agreed in a contract of sale.



Röchling Industrial SE & Co. KG

Röchlingstr. 1 • 49733 Haren (Ems)/Germany (DE) • Tel. +49 5934 701-0
info@roechling-plastics.com • www.roechling.com/industrial/haren

Print: 21/12/2024 • Release: 20/09/2023

PIM-Version: 725 • PIM-ID: 591123 • PIM-Code: 725-8-12.12.11.162-5.9.4-5

Page 2 / 2 (Dates in DD/MM/YYYY)

