

### Technical Data Sheet

# Polystone® G CubX® black

#### Typical characteristics

- High longitudinal and transversal stiffness
- Good handling
- Good thermal insulation
- Chemical resistant

#### Typical industries

- Construction de réservoirs et d'installations chimiques
- Traitement de l'eau potable et des eaux usées
- Réservoirs de stockage
- Construction de machines et d'installations
- Aquaculture

	Test method	Unit	Guideline value
<b>Properties for the full cross-ribbed twin-wall sheet</b>			
Thermal conductivity	ISO 8302   Tested with: GHP 500-1, Single-sheet process	W / (m * K)	Lambda 0,2
Densité	DIN EN ISO 1183	g / cm <sup>3</sup>	0,3
Area weight		kg/m <sup>2</sup>	18,6
Weld strength lattice / covering sheets		MPa	≥ 16
Flatness	DIN EN ISO 15860	mm/m	4
<b>Properties for the covering sheets</b>			
Density, RT	DIN EN ISO 1183	g / cm <sup>3</sup>	0,96
Yield stress	DIN EN ISO 527	MPa	24
Elongation at break	DIN EN ISO 527	%	> 50
Tensile modulus of elasticity	DIN EN ISO 527	MPa	1000
Notched impact strength	DIN EN ISO 179	kJ / m <sup>2</sup>	20
Dielectric constant	IEC 60250		2,5
Surface resistivity	DIN EN 62631-3-2		>10 <sup>14</sup>

The data stated above are average values ascertained by statistical tests on a regular basis. They are in accordance with DIN EN 15860. The data above are provided purely for information and shall not be regarded as binding unless expressly agreed in a contract of sale.

#### Röchling Industrial SE & Co. KG

Röchlingstr. 1 • 49733 Haren (Ems)/Germany (DE) • Tel. +49 5934 701-0  
 info@roechling-plastics.com • www.roechling.com/industrial/haren

Print: 21/11/2024 • Release: 20/09/2023

PIM-Version: 363 • PIM-ID: 591227 • PIM-Code: 363-35-11.20.11.33-7.6.7.5.5-5

Page 1 / 1 (Dates in DD/MM/YYYY)

