

### Technical Data Sheet

# Polystone<sup>®</sup> G vacuum formable natural

#### Typical characteristics

- Optimised shrink and contraction behaviour

#### Typical industries

- Healthcare

|  | Test method             | Unit                 | Guideline value   |
|--|-------------------------|----------------------|-------------------|
| <b>General properties</b>                          |                         |                      |                   |
| Water absorption                                   | DIN EN ISO 62           | %                    | <0,01             |
| Flammability (Thickness 3 mm / 6 mm)               | UL 94                   |                      | HB                |
| <b>Mechanical properties</b>                       |                         |                      |                   |
| Yield stress                                       | DIN EN ISO 527          | MPa                  | 22                |
| Elongation at break                                | DIN EN ISO 527          | %                    | >50               |
| Tensile modulus of elasticity                      | DIN EN ISO 527          | MPa                  | 1100              |
| Notched impact strength                            | DIN EN ISO 179          | kJ / m <sup>2</sup>  | 12                |
| Shore hardness                                     | DIN EN ISO 868          | scale D              | 63                |
| <b>Thermal properties</b>                          |                         |                      |                   |
| Thermal conductivity                               | DIN 52612-1             | W / (m * K)          | 0,40              |
| Thermal capacity                                   | DIN 52612               | kJ / (kg * K)        | 1,90              |
| Coefficient of linear thermal expansion            | DIN 53752               | 10 <sup>-6</sup> / K | 150 - 230         |
| Service temperature, long term                     | Average                 | °C                   | -50 ... 80        |
| Service temperature, short term (max.)             | Average                 | °C                   | 100               |
| Vicat softening temperature                        | DIN EN ISO 306, Vicat B | °C                   | 67                |
| <b>Electrical properties</b>                       |                         |                      |                   |
| Dielectric constant                                | IEC 60250               |                      | 2,5               |
| Dielectric dissipation factor (10 <sup>6</sup> Hz) | IEC 60250               |                      | 0,0004            |
| Volume resistivity                                 | DIN EN 62631-3-1        | Ω * cm               | >10 <sup>14</sup> |
| Surface resistivity                                | DIN EN 62631-3-2        |                      | >10 <sup>14</sup> |
| Comparative tracking index                         | IEC 60112               |                      | 600               |
| Dielectric strength                                | IEC 60243               | kV / mm              | 45                |

#### Röchling Industrial SE & Co. KG

Röchlingstr. 1 • 49733 Haren (Ems)/Germany (DE) • Tel. +49 5934 701-0  
[info@roechling-plastics.com](mailto:info@roechling-plastics.com) • [www.roechling.com/industrial/haren](http://www.roechling.com/industrial/haren)

Print: 27/07/2024 • Release: 20/09/2023

PIM-Version: 480 • PIM-ID: 591099 • PIM-Code: 480-50-8-9

