

Technical Data Sheet

Polystone[®] G virgin black - ASTM

Typical characteristics

- Easy to machine and weld
- Chemical resistance
- Good mechanical properties

Typical industries

- Химическая промышленность
- Машиностроение
- Строительная промышленность
- Аквакультура
- Подготовка питьевой воды и очистки сточных вод
- Резервуары для хранения химикатов

	Test method	Unit	Guideline value
General properties			
Density	ASTM D792	g / cm ³	0.953
Water Absorption	ASTM D570	%	<0.10
Mechanical properties			
Hardness	ASTM D2240	Shore D	65
Tensile Strength at yield 73°F	ASTM D638	psi	4000
Elongation at Break	ASTM D638	%	>500
Flexural Strength	ASTM D790	psi	181000
Izod Impact, Notched	ASTM D256	ft-lb/in	3.5
Coefficient of Friction, Dynamic			0.20-0.29
Thermal properties			
Coefficient of Linear Thermal Expansion	ASTM D696	in/in/°F x10 ⁻⁵	6
Melting Point		°F	268
Maximum Service Temperature, Air		°F	180
Heat Deflection Temperature 264psi	ASTM D648	°F	165
Flammability, UL94		1/8 inch	HB
Electrical properties			

Röchling Industrial Gastonia, LP

903 Gastonia Technology Parkway • 28034 Dallas/United States (US) • Tel. +1 704 922-7814
 info.gastonia@roechling.com • www.roechling.com/industrial/rep-us

Print: 27/07/2024 • Release: 20/09/2023

PIM-Version: 41 • PIM-ID: 717969 • PIM-Code: 41-19-11.27.16-7.5.8.5.6.7-2

Page 1 / 2 (Dates in DD/MM/YYYY)



	Test method	Unit	Guideline value
Dielectric constant	ASTM D150	1MHz	2.4
Surface resistivity	ASTM D257	Ω/cm	>10 ¹⁴
Compliance properties			
FDA			No
NSF			No
USDA			No

The data stated above are average values ascertained by statistical tests on a regular basis. The data above are provided purely for information and shall not be regarded as binding unless expressly agreed in a contract of sale.



Röchling Industrial Gastonia, LP

903 Gastonia Technology Parkway • 28034 Dallas/United States (US) • Tel. +1 704 922-7814
 info.gastonia@roechling.com • www.roechling.com/industrial/rep-us

Print: 27/07/2024 • Release: 20/09/2023

PIM-Version: 41 • PIM-ID: 717969 • PIM-Code: 41-19-11.27.16-7.5.8.5.6.7-2

Page 2 / 2 (Dates in DD/MM/YYYY)

