

### Technical Data Sheet

## Polystone<sup>®</sup> M AST + FDA black pressed

#### Typical characteristics

- Reduction of dust deposit
- Antistatic
- Good wear resistance
- Good impact strength

#### Typical industries

- Tecnologia di trasporto e automazione
- Ingegneria meccanica e impiantistica
- lavorazione carne, pesce e pollame
- Prodotti da forno o dolciari
- Industria delle bevande

|   | Test method             | Unit                  | Guideline value |
|---|-------------------------|-----------------------|-----------------|
| <b>General properties</b>               |                         |                       |                 |
| Density                                 | DIN EN ISO 1183-1       | g / cm <sup>3</sup>   | >0,94           |
| Water absorption                        | DIN EN ISO 62           | %                     | <0,01           |
| Flammability (Thickness 3 mm / 6 mm)    | UL 94                   |                       | HB              |
| Molecular weight                        | -                       | 10 <sup>6</sup> g/mol | ~ 9             |
| <b>Mechanical properties</b>            |                         |                       |                 |
| Yield stress                            | DIN EN ISO 527          | MPa                   | >20             |
| Elongation at break                     | DIN EN ISO 527          | %                     | >50             |
| Tensile modulus of elasticity           | DIN EN ISO 527          | MPa                   | >700            |
| Notched impact strength                 | DIN EN ISO 11542        | kJ / m <sup>2</sup>   | >50             |
| Shore hardness                          | DIN EN ISO 868          | scale D               | >63             |
| <b>Thermal properties</b>               |                         |                       |                 |
| Melting temperature                     | ISO 11357-3             | °C                    | 130 ... 135     |
| Thermal conductivity                    | DIN 52612-1             | W / (m * K)           | 0,40            |
| Thermal capacity                        | DIN 52612               | kJ / (kg * K)         | 1,90            |
| Coefficient of linear thermal expansion | DIN 53752               | 10 <sup>-6</sup> / K  | 150 ... 230     |
| Service temperature, long term          | Average                 | °C                    | -150 ... 80     |
| Service temperature, short term (max.)  | Average                 | °C                    | 130             |
| Vicat softening temperature             | DIN EN ISO 306, Vicat B | °C                    | 79              |

|                              | Test method      | Unit                     | Guideline value |
|------------------------------|------------------|--------------------------|-----------------|
| <b>Electrical properties</b> |                  |                          |                 |
| Volume resistivity           | DIN EN 62631-3-1 | $\Omega \cdot \text{cm}$ | $<10^9$         |
| Surface resistivity          | DIN EN 62631-3-2 | $\Omega$                 | $<10^9$         |

The data stated above are average values ascertained by statistical tests on a regular basis. They are in accordance with DIN EN 15860. The data above are provided purely for information and shall not be regarded as binding unless expressly agreed in a contract of sale.



#### Röchling Industrial SE & Co. KG

Röchlingstr. 1 • 49733 Haren (Ems)/Germany (DE) • Tel. +49 5934 701-0  
info@roechling-plastics.com • www.roechling.com/industrial/haren

Print: 21/11/2024 • Release: 27/10/2023 • Version: 2.0

PIM-Version: 690 • PIM-ID: 591219 • PIM-Code: 690-19-10.16.143.162-11.5.5.6-5

Page 2 / 2 (Dates in DD/MM/YYYY)

