

Technical Data Sheet

Polystone[®] M Naturel - ASTM

Typical characteristics

- Low coefficient of friction
- Very good abrasion and wear resistance
- Good impact strength

Typical industries

- Convoyage de matières en vrac
- Systèmes de convoyage et automatisé
- Industrie agroalimentaire

| | Test method | Unit | Guideline value |
|------------------------------------|-------------|---------------------|-----------------------|
| General properties | | | |
| Specific Gravity | ASTM D792 | g / cm ³ | 0.93 |
| Water Absorption | ASTM D570 | % | <0.10 |
| Mechanical properties | | | |
| Wear resistance | Sand-slurry | | 100 |
| Hardness | ASTM D2240 | Shore D | 62 - 66 |
| Tensile Strength at yield 73°F | ASTM D638 | psi | 3100 |
| Tensile Modulus | ASTM D638 | psi | 100000 |
| Elongation at Break | ASTM D638 | % | >350 |
| Flexural Strength | ASTM D790 | psi | 3500 |
| Compressive Strength | ASTM D695 | psi | 3000 |
| Izod Impact, Notched | ASTM D256 | ft-lb/in | No Break |
| Coefficient of Friction, Dynamic | | | 0.10-0.22 |
| Coefficient of Friction, Static | | | 0.15-0.20 |
| Izod Impact Strength | ASTM D4020 | kJ / m ² | 125 |
| Thermal properties | | | |
| CTE, linear | ASTM D696 | in/in/°F | 1.1x 10 ⁻⁴ |
| Melting Point | ASTM D3418 | °F | 266 - 275 |
| Vicat Softening Point | ISO306 | °F | 176 |
| Maximum Service Temperature, Air | | °F | 180 |
| Heat Deflection Temperature 264psi | ASTM D648 | °F | 108 |

Röchling Industrial Gastonia, LP

903 Gastonia Technology Parkway • 28034 Dallas/United States (US) • Tel. +1 704 922-7814
 info.gastonia@roechling.com • www.roechling.com/industrial/rep-us

Print: 27/07/2024 • Release: 31/05/2024 • Version: 3.0
 PIM-Version: 52 • PIM-ID: 717946 • PIM-Code: 52-19-11.121.161-6.11.5-2



| | Test method | Unit | Guideline value |
|------------------------------|-------------|--------------------|-----------------|
| Flammability, UL94 | | 1/8 inch | HB |
| Electrical properties | | | |
| Volume Resistivity | ASTM D257 | Ωcm | $>10^{15}$ |
| Dielectric constant | ASTM D150 | 1MHz | 2.3 |
| Dielectric strength | ASTM D149 | kV / mm | 45 |
| Surface resistivity | ASTM D257 | Ω/cm | $>10^{12}$ |
| Compliance properties | | | |
| FDA | | | Yes |
| NSF | | | No |
| USDA | | | Yes |

The data stated above are average values ascertained by statistical tests on a regular basis. The data above are provided purely for information and shall not be regarded as binding unless expressly agreed in a contract of sale.

