

Technical Data Sheet

Polystone[®] MPG black pressed

Typical characteristics

- Larga vida útil
- Buenas propiedades de deslizamiento con compañeros de deslizamiento suaves
- Baja absorción de humedad
- Buena resistencia al desgaste

Typical industries

- Construcción de máquinas e instalaciones
- Sistemas de transporte y automatización

	Test method	Unit	Guideline value
General properties			
Density	DIN EN ISO 1183-1	g / cm ³	>0,96
Water absorption	DIN EN ISO 62	%	<0,01
Flammability (Thickness 3 mm / 6 mm)	UL 94		HB
Molecular weight	-	10 ⁶ g/mol	~ 9
Mechanical properties			
Yield stress	DIN EN ISO 527	MPa	>20
Elongation at break	DIN EN ISO 527	%	>50
Tensile modulus of elasticity	DIN EN ISO 527	MPa	>700
Notched impact strength	DIN EN ISO 11542-2	kJ / m ²	>100
Shore hardness	DIN EN ISO 868	scale D	>65
Thermal properties			
Melting temperature	ISO 11357-3	°C	135
Thermal conductivity	DIN 52612-1	W / (m * K)	0,40
Thermal capacity	DIN 52612	kJ / (kg * K)	1,90
Coefficient of linear thermal expansion	DIN 53752	10 ⁻⁶ / K	150 ... 230
Service temperature, long term	Average	°C	-250 ... 80
Service temperature, short term (max.)	Average	°C	130 ... 135
Vicat softening temperature	DIN EN ISO 306, Vicat B	°C	79

Röchling Industrial SE & Co. KG

Röchlingstr. 1 • 49733 Haren (Ems)/Germany (DE) • Tel. +49 5934 701-0
info@roechling-plastics.com • www.roechling.com/industrial/haren

Print: 22/12/2024 • Release: 20/09/2023 • Version: 2.0

PIM-Version: 635 • PIM-ID: 591204 • PIM-Code: 635-27-15.11.12.143-5.11-5



	Test method	Unit	Guideline value
Electrical properties			
Volume resistivity	DIN EN 62631-3-1	$\Omega \cdot \text{cm}$	$>10^{14}$
Surface resistivity	DIN EN 62631-3-2	Ω	$>10^{14}$
Dielectric strength	IEC 60243	kV / mm	>40

The data stated above are average values ascertained by statistical tests on a regular basis. They are in accordance with DIN EN 15860. The data above are provided purely for information and shall not be regarded as binding unless expressly agreed in a contract of sale.



Röchling Industrial SE & Co. KG

Röchlingstr. 1 • 49733 Haren (Ems)/Germany (DE) • Tel. +49 5934 701-0
info@roechling-plastics.com • www.roechling.com/industrial/haren

Print: 22/12/2024 • Release: 20/09/2023 • Version: 2.0
 PIM-Version: 635 • PIM-ID: 591204 • PIM-Code: 635-27-15.11.12.143-5.11-5

