

Technical Data Sheet

Polystone[®] P (Copolymer) PG + UV-stabilized beige

Typical characteristics

- High mechanical strength
- Good weldability
- Good chlorine and UV resistant
- UV-resistant

Typical industries

- Sport e tempo libero

	Test method	Unit	Guideline value
General properties			
Density	DIN EN ISO 1183-1	g / cm ³	0,92
Water absorption	DIN EN ISO 62	%	<0,1
Flammability (Thickness 3 mm / 6 mm)	UL 94		HB
Mechanical properties			
Yield stress	DIN EN ISO 527	MPa	24
Elongation at break	DIN EN ISO 527	%	>50
Tensile modulus of elasticity	DIN EN ISO 527	MPa	1200
Notched impact strength	DIN EN ISO 179	kJ / m ²	> 30
Shore hardness	DIN EN ISO 868	scale D	68
Thermal properties			
Melting temperature	ISO 11357-3	°C	162 – 167
Thermal conductivity	DIN 52612-1	W / (m * K)	0,20
Thermal capacity	DIN 52612	kJ / (kg * K)	1,70
Coefficient of linear thermal expansion	DIN 53752	10 ⁻⁶ / K	120 - 190
Service temperature, long term	Average	°C	-30 ... 100
Service temperature, short term (max.)	Average	°C	150
Vicat softening temperature	DIN EN ISO 306, Vicat B	°C	85
Electrical properties			
Dielectric constant	IEC 60250		2,5
Dielectric dissipation factor (10 ⁶ Hz)	IEC 60250		0,00019

Röchling Industrial SE & Co. KG

Röchlingstr. 1 • 49733 Haren (Ems)/Germany (DE) • Tel. +49 5934 701-0
 info@roechling-plastics.com • www.roechling.com/industrial/haren

Print: 27/07/2024 • Release: 20/09/2023 • Version: 1.0
 PIM-Version: 41 • PIM-ID: 718605 • PIM-Code: 41-8-22.10.10.14-3-8



	Test method	Unit	Guideline value
Volume resistivity	DIN EN 62631-3-1	$\Omega \cdot \text{cm}$	$>10^{14}$
Surface resistivity	DIN EN 62631-3-2		$>10^{13}$
Comparative tracking index	IEC 60112		600
Dielectric strength	IEC 60243	kV / mm	45

Attention: Please see also product information

The data stated above are average values ascertained by statistical tests on a regular basis. They are in accordance with DIN EN 15860. The data above are provided purely for information and shall not be regarded as binding unless expressly agreed in a contract of sale.

