

Technical Data Sheet

Polystone[®] P copolymer grey - ASTM

Typical characteristics

- Chemical resistance
- High weldability
- Good impact strength

Typical industries

- Akvakultura
- Technika čistých prostor
- Technologie pitné a odpadní vody
- Výroba nádrží a zařízení pro chemický průmysl
- Skladovací nádrže
- Galvanizační zařízení
- Mořiny oceli
- Ventilační zařízení
- Zařízení pro čištění odpadního vzduchu

	Test method	Unit	Guideline value
General properties			
Density	ASTM D792	g / cm ³	0,91
Water Absorption	ASTM D570	%	≤0.1
Mechanical properties			
Hardness	ASTM D785	Shore D	69
Tensile Strength at yield 73°F	ASTM D638	psi	3500
Elongation at Break	ASTM D638	%	≥300
Flexural Strength	ASTM D790	psi	155,000
Compressive Strength	ASTM D695	psi	4000
Izod Impact, Notched	ASTM D256	ft-lb/in	8
Coefficient of Friction, Dynamic			0,25-0,28
Thermal properties			
Coefficient of Linear Thermal Expansion	ASTM D696	in/in/°F x10 ⁻⁵	6
Melting Point	ASTM D1525	°F	323
Maximum Service Temperature, Air		°F	180
Deflection Temperature at 1.8Mpa (264psi)	ASTM D648	°F	210



	Test method	Unit	Guideline value
Flammability, UL94		1/8 inch	HB
Electrical properties			
Dielectric constant	ASTM D150	1MHz	2,5
Dielectric strength	ASTM D149	V/mil	45
Surface resistivity	ASTM D257	Ω/cm	$\geq 10^{14}$
Compliance properties			
FDA			Yes
NSF			No
USDA			Yes

The data stated above are average values ascertained by statistical tests on a regular basis. The data above are provided purely for information and shall not be regarded as binding unless expressly agreed in a contract of sale.

