

Technical Data Sheet

Polystone[®] P copolymer natural - ASTM

Typical characteristics

- High weldability
- Chemical resistance
- Good impact strength

Typical industries

- Аквакультура
- Технологии чистых помещений
- Подготовка питьевой воды и очистки сточных вод
- Химическая промышленность
- Резервуары для хранения химикатов
- Гальванические установки
- Сталь-травильные установки
- Вентиляционные установки
- Установки очистки отработанного воздуха

	Test method	Unit	Guideline value
General properties			
Density	ASTM D792	g / cm ³	0.91
Water Absorption	ASTM D570	%	<0.10
Mechanical properties			
Hardness	ASTM D2240	Shore D	69
Tensile Strength at yield 73°F	ASTM D638	psi	3500
Elongation at Break	ASTM D638	%	≥300
Flexural Modulus	ASTM D790	psi	155000
Compressive Strength	ASTM D695	psi	4400
Izod Impact, Notched	ASTM D256	ft-lb/in	8.0
Coefficient of Friction, Dynamic			0.25-0.28
Thermal properties			
Coefficient of Linear Thermal Expansion	ASTM D696	in/in/°F x10 ⁻⁵	6
Melting Point		°F	323
Maximum Service Temperature, Air		°F	180

Röchling Industrial Gastonia, LP

903 Gastonia Technology Parkway • 28034 Dallas/United States (US) • Tel. +1 704 922-7814
 info.gastonia@roechling.com • www.roechling.com/industrial/rep-us

Print: 27/07/2024 • Release: 20/09/2023

PIM-Version: 43 • PIM-ID: 717966 • PIM-Code: 43-21-9.27.161-5.7.6.7.7.4.6.4.4-2



	Test method	Unit	Guideline value
Heat Deflection Temperature 264psi	ASTM D648	°F	210
Flammability, UL94		1/8 inch	HB
Electrical properties			
Dielectric constant	ASTM D150	1MHz	2.5
Dielectric strength	ASTM D149		45
Surface resistivity	ASTM D257	Ω/cm	≥10 ¹⁴
Compliance properties			
FDA			Yes
NSF			No
USDA			Yes

The data stated above are average values ascertained by statistical tests on a regular basis. The data above are provided purely for information and shall not be regarded as binding unless expressly agreed in a contract of sale.



Röchling Industrial Gastonia, LP

903 Gastonia Technology Parkway • 28034 Dallas/United States (US) • Tel. +1 704 922-7814
 info.gastonia@roechling.com • www.roechling.com/industrial/rep-us

Print: 27/07/2024 • Release: 20/09/2023

PIM-Version: 43 • PIM-ID: 717966 • PIM-Code: 43-21-9.27.161-5.7.6.7.4.6.4.4-2

