

Technical Data Sheet

Polystone[®] PPs (Homopolymer) white

Typical characteristics

- High stiffness
- Very good welding and processing properties
- Chemical resistance
- Flame retardant

Typical industries

- Construction de réservoirs et d'installations chimiques
- Technique des salles blanches
- Industrie électronique
- Stations de purification d'air
- Systèmes de ventilation
- Semiconductor Front-End applications
- Semiconductor Front-End Wet Bench

	Test method	Unit	Guideline value
General properties			
Water Absorption (after 48 hrs)	ASTM D570	%	<0.10
Densité	ASTM D792	g / cm ³	0.91
Mechanical properties			
Shore hardness	DIN EN ISO 868	scale D	>67
Hardness	ASTM D2240	Shore D	72
Tensile Strength at yield 73°F	ASTM D638	psi	4700
Izod Impact, Notched	ASTM D256	ft-lb/in	1
Coefficient of Friction, Dynamic			0.25-0.28
Thermal properties			
Coefficient of Linear Thermal Expansion	ASTM D696	in/in/°F x10 ⁻⁵	6
Melting Point		°F	323
Maximum Service Temperature, Air		°F	180
Heat Deflection Temperature 264psi	ASTM D648	°F	210
Flammability, UL94		1/8 inch	HB
Electrical properties			
Dielectric constant	ASTM D150	1MHz	2.4



	Test method	Unit	Guideline value
Dielectric strength	ASTM D149	kV / mm	45
Surface resistivity	ASTM D257	Ω/cm	$>10^{14}$
Compliance properties			
FDA			Yes
NSF			No
USDA			Yes

The data stated above are average values ascertained by statistical tests on a regular basis. They are in accordance with DIN EN 15860. The data above are provided purely for information and shall not be regarded as binding unless expressly agreed in a contract of sale.



Röchling Industrial Gastonia, LP

903 Gastonia Technology Parkway • 28034 Dallas/United States (US) • Tel. +1 704 922-7814
 info.gastonia@roechling.com • www.roechling.com/industrial/rep-us

Print: 27/07/2024 • Release: 07/05/2024 • Version: 3.0
 PIM-Version: 31 • PIM-ID: 753704 • PIM-Code: 31-24-131.12.27.10-7.7.8.4.4.10.9-5

