

### Technical Data Sheet

## Polystone<sup>®</sup> PPs CubX<sup>®</sup> (Homopolymer) grey

#### Typical characteristics

- High longitudinal and transversal stiffness
- Good handling
- Good thermal insulation
- Chemical resistant

#### Typical industries

- Construction de réservoirs et d'installations chimiques
- Stations de galvanisation
- Réservoirs de stockage
- Centres de décapage d'acier

	Test method	Unit	Guideline value
<b>Properties for the full cross-ribbed twin-wall sheet</b>			
Flammability	DIN 4102		BI (*)
Thermal conductivity	ISO 8302   Tested with: GHP 500-1, Single-sheet process	W / (m * K)	Lambda 0,18
Densité	DIN EN ISO 1183	g / cm <sup>3</sup>	0,315
Area weight		kg/m <sup>2</sup>	17,67
Weld strength lattice / covering sheets		MPa	≥ 20
Flatness	DIN EN ISO 15860	mm/m	≤ 3
<b>Properties for the covering sheets</b>			
Density, RT	DIN EN ISO 1183	g / cm <sup>3</sup>	0,94
Notched impact strength, RT	DIN EN ISO 179 EA1	kJ / m <sup>2</sup>	4
Melt flow rate (MFR) 2,16 kg, 230 °C	DIN EN ISO 1133	g / 10 min	0,45
Yield strain, RT	DIN EN ISO 527	%	7,19
Yield stress, RT	DIN EN ISO 527	N/mm <sup>2</sup>	32
Thermal properties, along, 150 °C	DIN EN ISO 15013	%	0,33
Thermal properties, transverse, 150 °C	DIN EN ISO 15013	%	0,17
Tensile modulus of elasticity, RT	DIN EN ISO 527	MPa	1300



(\*) tested on the covering sheets

The data stated above are average values ascertained by statistical tests on a regular basis. They are in accordance with DIN EN 15860. The data above are provided purely for information and shall not be regarded as binding unless expressly agreed in a contract of sale.



**Röchling Industrial SE & Co. KG**

Röchlingstr. 1 • 49733 Haren (Ems)/Germany (DE) • Tel. +49 5934 701-0  
info@roechling-plastics.com • www.roechling.com/industrial/haren

Print: 21/11/2024 • Release: 20/09/2023 • Version: 1.0  
PIM-Version: 258 • PIM-ID: 591217 • PIM-Code: 258-46-11.20.11.33-7.4.7.6-9

Page 2 / 2 (Dates in DD/MM/YYYY)

