

## Technical Data Sheet

# Polystone® PVDF natural pressed

### Typical characteristics

- High temperature resistance
- Good weldability
- Chemical resistant
- Good heat ageing resistance

### Typical industries

- 화학 가공 산업
- Clean-Room Technology
- 화학물질 저장 탱크
- 도금 공장
- 강철 산세 플랜트

	Test method	Unit	Guideline value
<b>General properties</b>			
Density	DIN EN ISO 1183-1	g / cm <sup>3</sup>	>1,75
Water absorption	DIN EN ISO 62	%	<0,4
Flammability (Thickness 3 mm / 6 mm)	UL 94		V0
<b>Mechanical properties</b>			
Yield stress	DIN EN ISO 527	MPa	>50
Elongation at break	DIN EN ISO 527	%	>30
Tensile modulus of elasticity	DIN EN ISO 527	MPa	>2100
Notched impact strength	DIN EN ISO 179	kJ / m <sup>2</sup>	>13
Shore hardness	DIN EN ISO 868	scale D	>75
<b>Thermal properties</b>			
Melting temperature	ISO 11357-3	°C	172 ... 175
Thermal conductivity	DIN 52612-1	W / (m * K)	0,19
Thermal capacity	DIN 52612	kJ / (kg * K)	1,20
Coefficient of linear thermal expansion	DIN 53752	10 <sup>-6</sup> / K	100 ... 140
Service temperature, long term	Average	°C	0 ... 140
Service temperature, short term (max.)	Average	°C	>145
Vicat softening temperature	DIN EN ISO 306, Vicat B	°C	140
<b>Electrical properties</b>			
Dielectric constant	IEC 60250		8,0



	Test method	Unit	Guideline value
Dielectric dissipation factor ( $10^6$ Hz)	IEC 60250		0,02
Volume resistivity	DIN EN 62631-3-1	$\Omega \cdot \text{cm}$	$>10^{14}$
Surface resistivity	DIN EN 62631-3-2	$\Omega$	$>10^{14}$
Comparative tracking index	IEC 60112		600
Dielectric strength	IEC 60243	kV / mm	20

The data stated above are average values ascertained by statistical tests on a regular basis. They are in accordance with DIN EN 15860. The data above are provided purely for information and shall not be regarded as binding unless expressly agreed in a contract of sale.



### Röchling Industrial SE & Co. KG

Röchlingstr. 1 • 49733 Haren (Ems)/Germany (DE) • Tel. +49 5934 701-0  
[info@roechling-plastics.com](mailto:info@roechling-plastics.com) • [www.roechling.com/industrial/haren](http://www.roechling.com/industrial/haren)

Print: 04/11/2024 • Release: 20/09/2023 • Version: 1.0

PIM-Version: 677 • PIM-ID: 591104 • PIM-Code: 677-106-11.16.33.31-7.7.4.6-5

Page 2 / 2 (Dates in DD/MM/YYYY)

