

## Technical Data Sheet

# Robadur<sup>®</sup> OS

### Typical characteristics

- UV-resistant
- Good sliding properties
- Good wear properties
- Oxidation inhibitory
- Low specific weight
- Chemical resistant
- High impact resistance
- High stiffness

### Typical industries

- Бумажная промышленность

	Test method	Unit	Guideline value
<b>General properties</b>			
Density	DIN EN ISO 1183-1	g / cm <sup>3</sup>	0,93
Water absorption	DIN EN ISO 62	%	<0,01
Flammability (Thickness 3 mm / 6 mm)	UL 94		HB / HB
Molecular weight		g/mol	9,2 * 10 <sup>6</sup>
Color			black
<b>Mechanical properties</b>			
Yield stress	DIN EN ISO 527	MPa	19
Elongation at break	DIN EN ISO 527	%	>200
Tensile modulus of elasticity	DIN EN ISO 527	MPa	540
Notched impact strength	DIN EN ISO 179/1eA	kJ / m <sup>2</sup>	>90
Shore hardness	DIN EN ISO 868 / 15 sec	scale D	63
<b>Thermal properties</b>			
Melting temperature	DIN EN ISO 3146	°C	135
Thermal conductivity	DIN EN ISO 8302	W / (m * K)	0,41
Thermal capacity	DIN 51005	kJ / (kg * K)	1,84
Coefficient of linear thermal expansion	DIN 53752	10 <sup>-6</sup> / K	200
Service temperature, long term	Average	°C	-250 ... 90

Röchling Industrial Oepping GmbH & Co. KG

Röchlingstr. 1 • 4151 Oepping/Austria (AT) • Tel. +43 7289 4611-0  
robaproducts@roechling.com • www.roechling.com/industrial/oepping

Print: 22/12/2024 • Release: 20/09/2023 • Version: 1.0

PIM-Version: 47 • PIM-ID: 709730 • PIM-Code: 47-9-15.223.126.9.17.33.18.132-8-6

Page 1 / 2 (Dates in DD/MM/YYYY)



	Test method	Unit	Guideline value
Service temperature, short term (max.)	Average	°C	110
<b>Electrical properties</b>			
Volume resistivity	DIN EN 62631-3-1	$\Omega \cdot \text{cm}$	$10^{10}$
Surface resistivity	DIN EN 62631-3-2	$\Omega$	$10^{10}$
Comparative tracking index	IEC 60112		600

The data given are standard values which are based on our experience & previous technical studies. These values are influenced by the design, processing conditions and environmental influences out of our control. The sustainability of the material for a given application is the responsibility of the user. Typing and printing errors reserved.

Chemical properties: chemically resistant to all aggressive media with the exception of highly oxidising acids. High resistant to corrosion. This material is resistant to all standard chemicals used in paper production, felt/wire cleaning and corrosion inhibition.

