

### Technical Data Sheet

# Robaflow<sup>®</sup> S

#### Typical characteristics

- High stiffness
- Chemical resistant

#### Typical industries

- Paper Industry

	Test method	Unit	Guideline value
<b>General properties</b>			
Density	DIN EN ISO 1183-1	g / cm <sup>3</sup>	1,06
Flammability	UL 94		HB
Moisture Absorption (23°C, 50% RH)	DIN EN ISO 62	%	0,06
<b>Mechanical properties</b>			
Yield stress	DIN EN ISO 527	MPa	30
Elongation at break	DIN EN ISO 527	%	>50
Tensile modulus of elasticity	DIN EN ISO 527	MPa	1500
Notched impact strength	ISO 179-1/1eA	kJ / m <sup>2</sup>	17
Shore hardness	DIN EN ISO 868	scale D	78
Ball indentation hardness (H358/30)	DIN EN ISO 2039-1	MPa	70
<b>Thermal properties</b>			
Coefficient of linear thermal expansion	DIN 53752	10 <sup>-6</sup> / K	70 - 90
Vicat softening temperature	DIN EN ISO 306, Vicat B	°C	115
<b>Electrical properties</b>			
Dielectric constant	IEC 60250		2,7
Volume resistivity	DIN EN 62631-3-1	Ω * cm	10 <sup>15</sup>
Surface resistivity	DIN EN 62631-3-2	Ω	>10 <sup>15</sup>

The data stated above are average values ascertained by statistical tests on a regular basis. They are in accordance with DIN EN 15860. The data above are provided purely for information and shall not be regarded as binding unless expressly agreed in a contract of sale.

