

## Technical Data Sheet

# Robaseal<sup>®</sup> L

### Typical characteristics

- Limited dry-running properties
- Good sliding properties

### Typical industries

- Papírenský průmysl

	Test method	Unit	Guideline value
<b>General properties</b>			
Density	DIN EN ISO 1183-1	g / cm <sup>3</sup>	1,25
Water absorption	DIN EN ISO 62	%	0,05
Coefficient of friction (against steel)	internal method: 2m/s; 1MPa	-	0,165
<b>Mechanical properties</b>			
Elongation at break	DIN EN ISO 527	%	5
Tensile modulus of elasticity	DIN EN ISO 527	MPa	1.400
Tensile strength	DIN EN ISO 527	MPa	15
Shore hardness	DIN EN ISO 868 / 15 sec	scale D	65
Flexural Strength		MPa	24
<b>Thermal properties</b>			
Thermal conductivity	DIN 52612-1	W / (m * K)	-
Coefficient of linear thermal expansion	DIN 53752	10 <sup>-6</sup> / K	115
Service temperature, long term	Average	°C	100

The data given are standard values which are based on our experience & previous technical studies. These values are influenced by the design, processing conditions and environmental influences out of our control. The sustainability of the material for a given application is the responsibility of the user. Typing and printing errors reserved.

