

## Technical Data Sheet

# Sustadur<sup>®</sup> PET TF - ASTM

### Typical industries

- 컨베이어 기술 및 자동화
- 기계 공학 산업
- 전자 제품
- 차량 제조
- Food Industry
- Bakery and Confectionery
- Beverage Industry

	Test method	Unit	Guideline value
<b>General properties</b>			
Density	ASTM D792	g / cm <sup>3</sup>	1.44
Water Absorption 24 hours	ASTM D570	%	0.06
Dissipation Factor	ASTM D150	1MHz	0.02
Water Absorption Saturation	ASTM D570	%	0.47
<b>Mechanical properties</b>			
Hardness	ASTM D2240	Shore D	80
Tensile Strength at yield 73°F	ASTM D638	psi	10500
Tensile Modulus	ASTM D638	psi	377000
Elongation at Break	ASTM D638	%	5
Flexural Strength	ASTM D790	psi	14000
Flexural Modulus	ASTM D790	psi	360000
Compressive Strength	ASTM D695	psi	15000
Rockwell Hardness	ASTM D785		94
Shear Strength	ASTM D732	psi	8500
Izod Impact, Notched	ASTM D256	ft-lb/in	0.4
Coefficient of Friction, Dynamic			0.19
<b>Thermal properties</b>			
Thermal Conductivity		in/hr/ft <sup>2</sup> /°F	1.9

### Röchling Industrial Gastonia, LP

903 Gastonia Technology Parkway • 28034 Dallas/United States (US) • Tel. +1 704 922-7814  
 info.gastonia@roechling.com • www.roechling.com/industrial/rep-us

Print: 27/07/2024 • Draft: 21/09/2023

PIM-Version: 26 • PIM-ID: 717917 • PIM-Code: 26-14-11.5.8.7.5.5.6-2



	Test method	Unit	Guideline value
Coefficient of Linear Thermal Expansion	ASTM D696	in/in/°F x10 <sup>-5</sup>	4.5
Melting Point	ASTM D789	°F	491
Continuous Service Temperature, Air		°F	210
Deflection Temperature at 1.8Mpa (264psi)	ASTM D648	°F	180
Deflection Temperature at 1.8Mpa (66psi)	ASTM D648	°F	338
Flammability, UL94		1/8 inch	HB
<b>Electrical properties</b>			
Dielectric constant	ASTM D150	1MHz	3.2
Dielectric strength	ASTM D149	V/mil	400
Surface resistivity	ASTM D257	Ω/cm	>10 <sup>13</sup>
<b>Compliance properties</b>			
NSF			No

The data stated above are average values ascertained by statistical tests on a regular basis. The data above are provided purely for information and shall not be regarded as binding unless expressly agreed in a contract of sale.

### Röchling Industrial Gastonia, LP

903 Gastonia Technology Parkway • 28034 Dallas/United States (US) • Tel. +1 704 922-7814  
[info.gastonia@roechling.com](mailto:info.gastonia@roechling.com) • [www.roechling.com/industrial/rep-us](http://www.roechling.com/industrial/rep-us)

Print: 27/07/2024 • Draft: 21/09/2023

PIM-Version: 26 • PIM-ID: 717917 • PIM-Code: 26-14-11.5.8.7.5.5.6-2

Page 2 / 2 (Dates in DD/MM/YYYY)

