

### Technical Data Sheet

## Sustamid® 66 MO - ASTM

#### Typical characteristics

- High abrasion resistance
- Good dimensional stability
- Good sliding properties

#### Typical industries

- Mechanical Engineering Industry
- Electronics
- Building industry

	Test method	Unit	Guideline value
<b>General properties</b>			
Density	ASTM D792	g / cm <sup>3</sup>	1.15
Water Absorption	ASTM D570	%	8.5
Water Absorption 24 hours	ASTM D570	%	1.0
Dissipation Factor	ASTM D150	1MHz	0.02
<b>Mechanical properties</b>			
Tensile Strength at Yield	ASTM D638	psi	12000
Hardness	ASTM D2240	Shore D	85
Tensile Modulus	ASTM D638	psi	450000
Tensile Elongation	ASTM D638	%	25
Flexural Strength	ASTM D790	psi	17000
Flexural Modulus	ASTM D790	psi	460000
Compressive Strength	ASTM D695	psi	16000
Rockwell Hardness	ASTM D785		85
Rockwell Hardness	ASTM D785	R	115
Shear Strength	ASTM D732	psi	10500
Izod Impact, Notched	ASTM D256	ft-lb/in	0.6
Coefficient of Friction, Dynamic			0.23
<b>Thermal properties</b>			
Thermal Conductivity		in/hr/ft <sup>2</sup> /°F	1.7
Coefficient of Linear Thermal Expansion	ASTM D696	in/in/°F x10 <sup>-5</sup>	4.0
Melting Point	ASTM D789	°F	495



	Test method	Unit	Guideline value
Continuous Service Temperature, Air		°F	220
Flammability, UL94		1/8 inch	HB
Deflection Temperature at 264psi	ASTM D648	°F	195
Deflection Temperature at 66psi	ASTM D648	°F	470
<b>Electrical properties</b>			
Dielectric constant	ASTM D150	1MHz	3.8
Dielectric strength	ASTM D149	V/mil	350
Surface resistivity	ASTM D257	Ω/cm	>10 <sup>13</sup>
<b>Compliance properties</b>			
FDA			No
NSF			No
USDA			No

The data stated above are average values ascertained by statistical tests on a regular basis. The data above are provided purely for information and shall not be regarded as binding unless expressly agreed in a contract of sale.

### Röchling Industrial Gastonia, LP

903 Gastonia Technology Parkway • 28034 Dallas/United States (US) • Tel. +1 704 922-7814  
[info.gastonia@roechling.com](mailto:info.gastonia@roechling.com) • [www.roechling.com/industrial/rep-us](http://www.roechling.com/industrial/rep-us)

Print: 27/07/2024 • Draft: 21/09/2023

PIM-Version: 29 • PIM-ID: 717975 • PIM-Code: 29-16-62.150.222-5.8.8-2

Page 2 / 2 (Dates in DD/MM/YYYY)

