

Technical Data Sheet

Sustamid[®] 6G OL - ASTM

Typical characteristics

- Self-lubricating
- Improved "stick-slip" properties
- high absorption of moisture of up to 3 % in standard atmosphere
- Good sliding properties

Typical industries

- Stavba strojů a zařízení
- Dopravní technika a automatizace

| | Test method | Unit | Guideline value |
|----------------------------------|-------------|---------------------------|-----------------|
| General properties | | | |
| Density | ASTM D792 | g / cm ³ | 1.15 |
| Water Absorption | ASTM D570 | % | 5.0 |
| Water Absorption 24 hours | ASTM D570 | % | 1.0 |
| Dissipation Factor | ASTM D150 | 1MHz | - |
| Mechanical properties | | | |
| Hardness | ASTM D2240 | Shore D | 74 |
| Tensile Strength at yield 73°F | ASTM D638 | psi | 11000 |
| Tensile Modulus | ASTM D638 | psi | 370000 |
| Elongation at Break | ASTM D638 | % | 30 |
| Flexural Strength | ASTM D790 | psi | 14000 |
| Flexural Modulus | ASTM D790 | psi | 380000 |
| Compressive Strength | ASTM D695 | psi | 13500 |
| Rockwell Hardness | ASTM D785 | | 85 |
| Rockwell Hardness | ASTM D785 | R | 115 |
| Shear Strength | ASTM D732 | psi | 8000 |
| Izod Impact, Notched | ASTM D256 | ft-lb/in | 1.2 |
| Coefficient of Friction, Dynamic | | | 0.12 |
| Thermal properties | | | |
| Thermal Conductivity | | in/hr/ft ² /°F | 1.7 |



| | Test method | Unit | Guideline value |
|---|-------------|----------------------------|-------------------|
| Coefficient of Linear Thermal Expansion | ASTM D696 | in/in/°F x10 ⁻⁵ | 5.0 |
| Melting Point | | °F | 430 |
| Continuous Service Temperature, Air | | °F | 210 |
| Flammability, UL94 | | 1/8 inch | HB |
| Deflection Temperature at 264psi | ASTM D648 | °F | 200 |
| Deflection Temperature at 66psi | ASTM D648 | °F | 380 |
| Electrical properties | | | |
| Dielectric constant | ASTM D150 | 1MHz | 3.7 |
| Dielectric strength | ASTM D149 | V/mil | 500 |
| Surface resistivity | ASTM D257 | Ω/cm | >10 ¹³ |
| Compliance properties | | | |
| FDA | | | No |
| NSF | | | No |
| USDA | | | No |

The data stated above are average values ascertained by statistical tests on a regular basis. The data above are provided purely for information and shall not be regarded as binding unless expressly agreed in a contract of sale.

Röchling Industrial Gastonia, LP

903 Gastonia Technology Parkway • 28034 Dallas/United States (US) • Tel. +1 704 922-7814
 info.gastonia@roechling.com • www.roechling.com/industrial/rep-us

Print: 27/07/2024 • Draft: 21/09/2023

PIM-Version: 29 • PIM-ID: 717919 • PIM-Code: 29-17-9.10.9.222-5.11-2

Page 2 / 2 (Dates in DD/MM/YYYY)

