

Technical Data Sheet

Sustamid[®] 6G blue - ASTM

Typical industries

- Construcción de máquinas e instalaciones
- Sector de la construcción
- Sistemas de transporte y automatización
- Construcción de vehículos
- Petróleo y gas
- Industria alimentaria
- Productos de bollería y dulces
- Energía eólica

	Test method	Unit	Guideline value
General properties			
Density	ASTM D792	g / cm ³	1.14
Water Absorption	ASTM D570	%	8.5
Water Absorption 24 hours	ASTM D570	%	1.0
Mechanical properties			
Hardness	ASTM D2240	Shore D	78
Tensile Strength at yield 73°F	ASTM D638	psi	12000
Tensile Modulus	ASTM D638	psi	400000
Elongation at Break	ASTM D638	%	25
Flexural Strength	ASTM D790	psi	15000
Flexural Modulus	ASTM D790	psi	420000
Compressive Strength	ASTM D695	psi	15500
Rockwell Hardness	ASTM D785		85
Rockwell Hardness	ASTM D785	R	115
Shear Strength	ASTM D732	psi	10500
Izod Impact, Notched	ASTM D256	ft-lb/in	0.6
Coefficient of Friction, Dynamic			0.22



	Test method	Unit	Guideline value
Thermal properties			
Thermal Conductivity		in/hr/ft ² /°F	1.7
Coefficient of Linear Thermal Expansion	ASTM D696	in/in/°F x10 ⁻⁵	4.5
Melting Point		°F	450
Continuous Service Temperature, Air		°F	230
Flammability, UL94		1/8 inch	HB
Deflection Temperature at 264psi	ASTM D648	°F	195
Deflection Temperature at 66psi	ASTM D648	°F	370
Electrical properties			
Dielectric constant	ASTM D150	1MHz	3.8
Dielectric strength	ASTM D149	V/mil	500
Surface resistivity	ASTM D257	Ω/cm	>10 ¹³
Compliance properties			
FDA			No
NSF			No
USDA			No

The data stated above are average values ascertained by statistical tests on a regular basis. The data above are provided purely for information and shall not be regarded as binding unless expressly agreed in a contract of sale.

Roechling Industrial Gastonia, LP

903 Gastonia Technology Parkway • 28034 Dallas/United States (US) • Tel. +1 704 922-7814
 info.gastonia@roechling.com • www.roechling.com/industrial/rep-us

Print: 27/07/2024 • Draft: 21/09/2023

PIM-Version: 25 • PIM-ID: 717959 • PIM-Code: 25-17-5.8.11.7.5.5.5.10-2

Page 2 / 2 (Dates in DD/MM/YYYY)

