

## Technical Data Sheet

# Sustarin<sup>®</sup> C ESD 90 - ASTM

### Typical characteristics

- Anti estático
- Sin negro de humo
- Buenas propiedades de deslizamiento

### Typical industries

- Tecnología de salas blancas
- Semiconductor Industry
- Sistemas de transporte y automatización

	Test method	Unit	Guideline value
<b>General properties</b>			
Density	ASTM D792	g / cm <sup>3</sup>	1.33
Water Absorption 24 hours	ASTM D570	%	1.0
Dissipation Factor	ASTM D150	1MHz	0.005
Water Absorption Saturation	ASTM D570	%	2.0
<b>Mechanical properties</b>			
Hardness	ASTM D2240	Shore D	86
Tensile Strength at yield 73°F	ASTM D638	psi	11000
Tensile Modulus	ASTM D638	psi	425000
Elongation at Break	ASTM D638	%	30
Flexural Strength	ASTM D790	psi	18000
Flexural Modulus	ASTM D790	psi	450000
Compressive Strength	ASTM D695	psi	8,000
Rockwell Hardness	ASTM D785		86
Rockwell Hardness	ASTM D785	R	120
Shear Strength	ASTM D732	psi	6,000
Izod Impact, Notched	ASTM D256	ft-lb/in	1.0-1.8
Coefficient of Friction, Dynamic			0.2
<b>Thermal properties</b>			
Thermal Conductivity		in/hr/ft <sup>2</sup> /°F	1.7
Coefficient of Linear Thermal Expansion	ASTM D696	in/in/°F x10 <sup>-5</sup>	4.8
Melting Point		°F	330



	Test method	Unit	Guideline value
Continuous Service Temperature, Air		°F	180
Deflection Temperature at 1.8Mpa (264psi)	ASTM D648	°F	250
Flammability, UL94		1/8 inch	HB
<b>Electrical properties</b>			
Dielectric constant	ASTM D150	1MHz	3.7
Dielectric strength	ASTM D149	V/mil	400
Surface resistivity	ASTM D257	Ω/cm	10 <sup>9-10<sup>11</sup></sup>
<b>Compliance properties</b>			
FDA			No
NSF			No
USDA			No

The data stated above are average values ascertained by statistical tests on a regular basis. The data above are provided purely for information and shall not be regarded as binding unless expressly agreed in a contract of sale.

