

## Technical Data Sheet

# Sustarin<sup>®</sup> C MG - ASTM

### Typical characteristics

- High mechanical strength
- High stiffness
- Good impact strength
- Multi-sterilisable with hot steam, plasma as well as ethylene oxide
- Low moisture absorption

### Typical industries

- Healthcare
- Farmacie

	Test method	Unit	Guideline value
<b>General properties</b>			
Density	ASTM D792	g / cm <sup>3</sup>	1.41
Water Absorption	ASTM D570	%	0.9
Water Absorption 24 hours	ASTM D570	%	0.2
<b>Mechanical properties</b>			
Hardness	ASTM D2240	Shore D	85
Tensile Strength at yield 73°F	ASTM D638	psi	9500
Tensile Modulus	ASTM D638	psi	400000
Elongation at Break	ASTM D638	%	40
Flexural Strength	ASTM D790	psi	12000
Flexural Modulus	ASTM D790	psi	400000
Rockwell Hardness	ASTM D785		88
Rockwell Hardness	ASTM D785	R	120
Izod Impact, Notched	ASTM D256	ft-lb/in	1.2
Coefficient of Friction, Dynamic			0.21
<b>Thermal properties</b>			
Thermal Conductivity		in/hr/ft <sup>2</sup> /°F	1.6
Coefficient of Linear Thermal Expansion	ASTM D696	in/in/°F x10 <sup>-5</sup>	5.5
Melting Point		°F	330
Continuous Service Temperature, Air		°F	180

### Roehling Industrial Gastonia, LP

903 Gastonia Technology Parkway • 28034 Dallas/United States (US) • Tel. +1 704 922-7814  
 info.gastonia@roehling.com • www.roehling.com/industrial/rep-us

Print: 03/09/2024 • Release: 08/04/2024 • Version: 1.0  
 PIM-Version: 43 • PIM-ID: 717932 • PIM-Code: 43-15-23.132.162.12-9.9-2



	Test method	Unit	Guideline value
Deflection Temperature at 1.8Mpa (264psi)	ASTM D648	°F	225
Deflection Temperature at 1.8Mpa (66psi)	ASTM D648	°F	320
Flammability, UL94		1/8 inch	HB
<b>Electrical properties</b>			
Surface resistivity	ASTM D257	Ω/cm	10 <sup>16</sup>
<b>Compliance properties</b>			
FDA			Yes

The data stated above are average values ascertained by statistical tests on a regular basis. The data above are provided purely for information and shall not be regarded as binding unless expressly agreed in a contract of sale.

