

Technical Data Sheet

Sustarin[®] C PIR black

Typical characteristics

- Sustainable Plastic
- Chemical resistance
- Low moisture absorption
- High abrasion resistance
- ideal combination of tensile strength, stiffness and impact strength
- Low creep tendency
- Good machinability
- favourable electric and dielectric behaviour
- Good dimensional stability
- Good sliding properties

Typical industries

- Машиностроение
- Нефтегазовая отрасль
- Конвейерные технологии и автоматизация
- Электронная промышленность
- Строительство транспортных средств
- Сельское Хозяйство
- Возобновляемая энергия

	Test method	Unit	Guideline value
General properties			
Density	DIN EN ISO 1183-1	g / cm ³	1,41
Water absorption	DIN EN ISO 62	%	0,2
Flammability	UL 94		HB/HB
Mechanical properties			
Yield stress	DIN EN ISO 527	MPa	65
Elongation at break	DIN EN ISO 527	%	30
Tensile modulus of elasticity	DIN EN ISO 527	MPa	2700
Notched impact strength	DIN EN ISO 179	kJ / m ²	6
Shore hardness	DIN EN ISO 868	scale D	80
Thermal properties			
Melting temperature	ISO 11357-3	°C	165
Thermal conductivity	DIN 52612-1	W / (m * K)	0,31
Thermal capacity	DIN 52612	kJ / (kg * K)	1,50
Coefficient of linear thermal expansion	DIN 53752	10 ⁻⁶ / K	110

Röchling Industrial Lahnstein SE & Co. KG

Sustaplast-Str. 1 • 56112 Lahnstein/Germany (DE) • Tel. +49 2621 693-0
 info.lahnstein@roechling.com • www.roechling.com/industrial/lahnstein

Print: 22/07/2024 • Release: 18/07/2024 • Version: 4.0

PIM-Version: 154 • PIM-ID: 753713 • PIM-Code: 154-23-10.27.11.62.17.11.69.9.150.222-5.5.11.8.7.6.6

Page 1 / 2 (Dates in DD/MM/YYYY)



	Test method	Unit	Guideline value
Service temperature, long term	Average	°C	-50...100
Service temperature, short term (max.)	Average	°C	140
Heat deflection temperature	DIN EN ISO 75, Verf. A, HDT	°C	110
Electrical properties			
Dielectric constant	IEC 60250		3,8
Dielectric dissipation factor (50 Hz)	IEC 60250		0,002
Volume resistivity	DIN EN 62631-3-1	$\Omega \cdot \text{cm}$	10^{13}
Surface resistivity	DIN EN 62631-3-2		10^{13}
Comparative tracking index	IEC 60112		600
Dielectric strength	IEC 60243	kV / mm	40

