

### Technical Data Sheet

## Sustarin<sup>®</sup> C brown

#### Typical characteristics

- Resistencia química
- Baja absorción de humedad
- Alta resistencia a la abrasión
- Alta resistencia a la tracción
- Alta rigidez
- Buena resistencia al impacto
- Baja tendencia a la fluencia
- Buena maquinabilidad
- Buenas propiedades eléctricas
- Excelente rigidez dieléctrica
- Buena estabilidad dimensional
- Buenas propiedades de deslizamiento

#### Typical industries

- Sistemas de transporte y automatización
- Construcción de máquinas e instalaciones
- Electrónica
- Construcción de vehículos
- Healthcare
- Industria alimentaria
- Procesamiento de carne, pescado y aves de corral
- Productos de bollería y dulces

|   | Test method       | Unit                 | Guideline value |
|---|-------------------|----------------------|-----------------|
| <b>General properties</b>               |                   |                      |                 |
| Density                                 | DIN EN ISO 1183-1 | g / cm <sup>3</sup>  | 1,41            |
| Water absorption                        | DIN EN ISO 62     | %                    | 0,2             |
| Flammability (Thickness 3 mm / 6 mm)    | UL 94             |                      | HB / HB         |
| <b>Mechanical properties</b>            |                   |                      |                 |
| Yield stress                            | DIN EN ISO 527    | MPa                  | 67              |
| Elongation at break                     | DIN EN ISO 527    | %                    | 30              |
| Tensile modulus of elasticity           | DIN EN ISO 527    | MPa                  | 2800            |
| Notched impact strength                 | DIN EN ISO 179    | kJ / m <sup>2</sup>  | 6               |
| Shore hardness                          | DIN EN ISO 868    | scale D              | 81              |
| <b>Thermal properties</b>               |                   |                      |                 |
| Melting temperature                     | ISO 11357-3       | °C                   | 165             |
| Thermal conductivity                    | DIN 52612-1       | W / (m * K)          | 0,31            |
| Thermal capacity                        | DIN 52612         | kJ / (kg * K)        | 1,50            |
| Coefficient of linear thermal expansion | DIN 53752         | 10 <sup>-6</sup> / K | 110             |

|  | Test method                 | Unit    | Guideline value  |
|--|-----------------------------|---------|------------------|
| Service temperature, long term         | Average                     | °C      | -50 ... 100      |
| Service temperature, short term (max.) | Average                     | °C      | 140              |
| Heat deflection temperature            | DIN EN ISO 75, Verf. A, HDT | °C      | 110              |
| <b>Electrical properties</b>           |                             |         |                  |
| Dielectric constant                    | IEC 60250                   |         | 3,8              |
| Dielectric dissipation factor (50 Hz)  | IEC 60250                   |         | 0,002            |
| Volume resistivity                     | DIN EN 62631-3-1            | Ω * cm  | 10 <sup>13</sup> |
| Surface resistivity                    | DIN EN 62631-3-2            | Ω       | 10 <sup>13</sup> |
| Comparative tracking index             | IEC 60112                   |         | 600              |
| Dielectric strength                    | IEC 60243                   | kV / mm | 40               |

The short-term maximum application temperature only applies to very low mechanical stress for a few hours. The long-term maximum application temperature is based on the thermal ageing of plastics by oxidation, resulting in a decrease of the mechanical properties. This applies to an exposure to temperatures for at least 5.000 hours causing a 50% loss of the tensile strength from the original value (measured at room temperature). This value says nothing about the mechanical strength of the material at high application temperatures. In case of thick-walled parts, only the surface layer is affected by oxidation from high temperatures. With the addition of antioxidants, a better protection of the surface layer is achieved. In any case, the center area of the material remains unaffected. The minimum application temperature is basically influenced by possible stress factors like impact and/or shock under application. The values stated refer to a minimum degree of impact stress. The electrical properties as stated result from measurements on natural, dry material. With other colours (in particular black) or saturated material, there may be clear differences in the electrical properties. The data stated above are average values ascertained by statistical tests on a regular basis. They are in accordance with DIN EN 15860. They serve as information about our products and are presented as a guide to choose from our range of materials. This, however, does not include an assurance of specific properties or the suitability for particular application purposes that are legally binding. Since the properties also depend on the dimension of the semi-finished products and the degree of crystallization (e.g. nucleating by pigments), the actual values of the properties of a particular product may differ from the indicated values.

