

## Technical Data Sheet

# Sustarin<sup>®</sup> H - ASTM

### Typical characteristics

- Good dimensional stability
- Low moisture absorption
- Good wear resistance
- high mechanical strength, stiffness and toughness
- high creep resistance
- Good machinability

### Typical industries

- 컨베이어 기술 및 자동화
- 기계 공학 산업
- 전자 제품

	Test method	Unit	Guideline value
<b>General properties</b>			
Density	ASTM D792	g / cm <sup>3</sup>	1.42
Water Absorption	ASTM D570	%	0.7
Water Absorption 24 hours	ASTM D570	%	0.2
<b>Mechanical properties</b>			
Tensile Strength at yield 73°F	ASTM D638	psi	10500
Tensile Modulus	ASTM D638	psi	420000
Elongation at Break	ASTM D638	%	40
Flexural Strength	ASTM D790	psi	12000
Flexural Modulus	ASTM D790	psi	400000
Compressive Strength	ASTM D695	psi	16000
Rockwell Hardness	ASTM D785		94
Rockwell Hardness	ASTM D785	R	122
Shear Strength	ASTM D732	psi	9000
Izod Impact, Notched	ASTM D256	ft-lb/in	1.2
Coefficient of Friction, Dynamic			0.12
<b>Thermal properties</b>			
Thermal Conductivity		in/hr/ft <sup>2</sup> /°F	2.0
Coefficient of Linear Thermal Expansion	ASTM D696	in/in/°F x10 <sup>-5</sup>	6.7

### Röchling Industrial Gastonia, LP

903 Gastonia Technology Parkway • 28034 Dallas/United States (US) • Tel. +1 704 922-7814  
 info.gastonia@roechling.com • www.roechling.com/industrial/rep-us

Print: 27/07/2024 • Draft: 21/09/2023

PIM-Version: 25 • PIM-ID: 717936 • PIM-Code: 25-14-150.11.142.10.10.69-11.5.8-2



	Test method	Unit	Guideline value
Melting Point		°F	347
Continuous Service Temperature, Air		°F	185
Deflection Temperature at 1.8Mpa (264psi)	ASTM D648	°F	242
Deflection Temperature at 1.8Mpa (66psi)	ASTM D648	°F	290
Flammability, UL94		1/8 inch	HB
<b>Electrical properties</b>			
Dielectric constant	ASTM D150	1MHz	3.1
Dielectric strength	ASTM D149	V/mil	400
Surface resistivity	ASTM D257	Ω/cm	10 <sup>16</sup>
<b>Compliance properties</b>			
FDA			Yes
NSF			No
USDA			Yes

The data stated above are average values ascertained by statistical tests on a regular basis. The data above are provided purely for information and shall not be regarded as binding unless expressly agreed in a contract of sale.

### Röchling Industrial Gastonia, LP

903 Gastonia Technology Parkway • 28034 Dallas/United States (US) • Tel. +1 704 922-7814  
 info.gastonia@roechling.com • www.roechling.com/industrial/rep-us

Print: 27/07/2024 • Draft: 21/09/2023

PIM-Version: 25 • PIM-ID: 717936 • PIM-Code: 25-14-150.11.142.10.10.69-11.5.8-2

Page 2 / 2 (Dates in DD/MM/YYYY)

