

## Technisches Datenblatt

# Glastherm<sup>®</sup> HT 250 HQ - ASTM

### Typische Eigenschaften

- Niedrige Wärmeleitfähigkeit und sehr hohe Temperaturbeständigkeit
- Faserverbundwerkstoff entwickelt für Anwendungen im Bereich der thermischen Isolierung (max. Dauereinsatztemperatur 250°C)
- Reduces Heat Loss

### Typische Industrien

- Chemischer Behälter- und Anlagenbau
- Maschinen- und Anlagenbau
- Pipelines
- Öl und Gas

	Testverfahren	Einheit	Wert
<b>Allgemeine Eigenschaften</b>			
Standard Color			Light Green
Maximum Service Temp.		°C	400
Continuous Use Temp.		°C	250
<b>Mechanische Eigenschaften</b>			
Flexural Strength	ASTM D 790	psi	87,000
Compressive Strength @RT	ASTM D 695	psi	87,000
Compressive Strength @356°F / 180°C	ASTM D 695	psi	72,500
<b>Thermische Eigenschaften</b>			
Coefficient of Thermal Expansion Across Thickness	ASTM D 696	(in./in.°C) x 10 <sup>-5</sup>	11.6
Coefficient of Thermal Expansion Across Surface	ASTM D 696	(in./in.°C) x 10 <sup>-5</sup>	1.3
Wärmeleitfähigkeit	ASTM C 177		1.54
<b>Physikalische Eigenschaften</b>			
Dichte	ASTM D 792	lbs/ft <sup>3</sup>	125
Water Absorption	ASTM D 570	% by wt.	<0.10
Thickness Tolerance		inches	+/-0.004
<b>Dielektrische Eigenschaften</b>			



	Testverfahren	Einheit	Wert
Electrical Strength - Perpendicular S/T in Air	ASTM D 149	Vpm	300

All of the information, suggestions, and recommendations pertaining to the properties and uses of the Röchling Glastic Composites products described herein are based upon tests and data believed to be accurate; however, the final determination regarding the suitability of any material described herein for the use contemplated, the manner of such use, and whether the use infringes any patents is the sole responsibility of the user. THERE IS NO WARRANTY, EXPRESS OR IMPLIED, INCLUDING, WITHOUT LIMITATION WARRANTY OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE. Under no circumstances shall we be liable for incidental or consequential loss or damage. Glastic® is a registered trademark of Röchling Glastic Composites. UL® is a registered trademark of Underwriters Laboratories, Inc.



**Röchling Industrial Cleveland, LP**

4321 Glenridge Road • 44121 Cleveland/United States (US) • Tel. +1 216 486-0100  
[info@glastic.com](mailto:info@glastic.com) • [www.roechling.com/cleveland](http://www.roechling.com/cleveland)

Print: 27/07/2024 • Release: 11/10/2023 • Version: 2.0  
 PIM-Version: 47 • PIM-ID: 715301 • PIM-Code: 47-25-6.9.6-7.5.5.5-6

